

BENTONITE IN OREGON: OCCURRENCES, ANALYSES, AND ECONOMIC POTENTIAL

1989

STATE OF OREGON
DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES
DONALD A. HULL, STATE GEOLOGIST

STATE OF OREGON DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES 910 State Office Building 1400 SW Fifth Avenue Portland, Oregon 97201

SPECIAL PAPER 20

BENTONITE IN OREGON: OCCURRENCES, ANALYSES, AND ECONOMIC POTENTIAL

By Jerry J. Gray, Ronald P. Geitgey, and Gary L. Baxter, Oregon Department of Geology and Mineral Industries

1989

Conducted in conformance with ORS 516.030



GOVERNING BOARD	
Donald A. Haagensen, Chair	Portland
Sidney R. Johnson	Baker
	tle Creek

STATE GEOLOGIST Donald A. Hull DEPUTY STATE GEOLOGIST John D. Beaulieu

Oregon Department of Geology and Mineral Industries Special Papers, ISSN 0278-3703.

CONTENTS

SUMMA	ARY	age 1
INTRO	DUCTION Bentonite, the rock, defined	2
	Bentonite, the rock, defined Purpose	2
	Scope	2
NATIO	NAL INDUSTRY STRUCTURE	
	Introduction Bentonite	
	Fuller's earth	3
	Drilling mud Iron-ore pelletizing	4
	Foundry sand binder Oil and grease absorbent and pet litter Miscellaneous	4
	Exports U.S. exports	5
OREGO	ON INDUSTRY STRUCTURE	7
	Central Oregon Bentonite Teague Mineral Products Mining and milling of bentonite	7
BENTO	NITE DEPOSIT MODELS	8
SURVE	YING OF OREGON BENTONITES Existing data Field surveying Observations made during field survey and laboratory work	9
	Compilation geologic map showing sample locations and basin outlines (Plate 2)	9
LABOR	ATORY TESTING Samples	12
	Testing rationale Sample preparation (pitfalls) Quality control	12 12
RESUL	TS	
	Overview	13
FUTUE	RE STUDIES	14
REFER	ENCES	15
APPEN	DIXES	17
	Sample preparation X-ray diffraction procedures and interpretation Moisture content	17
	4. Swell (percent expansion) 5. Grit	18
	6. Water loss	20 23
	8. Trial tests	26 27

ILLUSTRATIONS

	Pa	ge
1. 2. 3. 4. 5. 6. 7. 8.	Bentonite sold or used by domestic producers for specified uses Fuller's earth sold or used by domestic producers for specified uses Bentonite (including Ca-bentonite/fuller's earth) sold or used by domestic producers for specified uses Oregon bentonite producers' mines and mills Teague Mineral Products mill Bentonite outcrop (site 40) with popcorn weathering surface Bentonite outcrop (site 65) with alligator hide weathering Hand augering of unvegetated hillside (sites 40-44) with bentonite outcrops Photograph showing shallow sampling trenching during taking of sample 12	3 4 7 7 9 10
1. 2. 3. 4. 5. 6. 7. 8. 9.	Bentonite (Na- and Ca-bentonite) and fuller's earth (Ca-bentonite) sold or used by domestic producers, listed by kind and by use	5 6 3) 13 19 20 21 22 24 25 26 26
15. PL 1. 2.	ATES (folded separately) Bentonite (Na- and Ca-bentonite) and fuller's earth (Ca-bentonite) sold or used (Table 1) Compilation geologic map of eastern Oregon and portions of western Oregon showing sample locations and geologic un deposited in basins Survey data, Oregon bentonite study (Table 4)	28

COVER PHOTO

View is looking westerly from a bluff near the Mascall Ranch, Grant County, at outcrops of the Miocene-age Mascall Formation, which contains bentonite beds. Samples 34-39 were taken from this general area.

BENTONITE IN OREGON: OCCURRENCES, ANALYSES, AND ECONOMIC POTENTIAL

SUMMARY

Analysis of the 152 samples collected for this study from various geological basins ranging in age from approximately 4 to 40 million years shows that exploration opportunities for commercial bentonite deposits exist in Oregon. Preliminary laboratory analyses show that Oregon bentonites have a wide variety of physical properties including degrees of swell, water loss, and grit content that could serve a wide spectrum of industrial uses. The potential for large-size deposits exists in the state. Some samples, for example, were taken from outcrops that had thicknesses of tens of feet. Because of its location, Oregon bentonite could offer transportation advantages to markets on the West Coast and in Pacific Rim countries.

Laboratory research conducted for this study identified some sources of error in testing bentonite. Sample preparation was shown to affect physical properties such as water loss and presumably other properties such as viscosity. Previous studies (Wolfbauer, 1977; Auer and Thayer, 1978) mentioned the possibility that sample preparation could affect physical properties but did not describe it in detail.

National and state production and marketing data on bentonite were used in this study to determine the potential size of markets for bentonite from Oregon. Each year, 150,000 to 200,000 tons of bentonite produced in Wyoming and Montana are exported from Pacific Northwest ports. Between 1958 and 1986, two Oregon bentonite manufacturers also produced a total of about 185,000 tons that they sold to a wide range of markets. This study indicates that there are West Coast and Pacific Rim bentonite markets that Oregon could supply.

INTRODUCTION

BENTONITE, THE ROCK, DEFINED

Bentonite is a rock name for a claystone that consists mainly of the mineral species montmorillonite with varying ratios of sodium (Na) to calcium (Ca) to other exchangeable ions of the mineral group smectite. Bentonites are divided into two general classes: those that swell extensively and form a gel (Na-montmorillonite) when mixed with water, and those that do not swell appreciably (Ca-montmorillonite) or form a gel when wetted.

BENTONITE, THE COMMODITY, DEFINED

The terms "sodium bentonite" (Na-bentonite) and "calcium bentonite" (Ca-bentonite) are used as names for the swelling and nonswelling forms, respectively, of the industry commodity bentonite. The mineral terms "smectite" and "montmorillonite" are seldom used by the bentonite industry. For some segments of the clay industry, the term "fuller's earth" is used interchangeably with the term "Ca-bentonite." According to Patterson and Murray (1983), most but not all fuller's earth deposits are actually bentonite. The term "fuller's earth" comes from its first use, which was cleaning or "fulling" wool (removing the lanolin and dirt) by fullers. In the United States, the term "fuller's earth" is applied to clay or other fine-grained earthy material suitable for such uses as bleaching, absorbing, decolorizing and purifying oils, and petroleum processing. In European commerce, the term "fuller's carth" is used only for Ca-montmorillonite.

PURPOSE

The purpose of this study was to conduct a statewide reconnaissance survey of Oregon bentonite that could serve as a guide for additional exploration by industry and realistic planning by government entities. This bentonite study is one of a series of industrial commodity studies that have been or currently are being conducted by the Oregon Department of Geology and Mineral Industries (DOGAMI).

Mineral-resource development offers substantial opportunity for diversification of the state's economy, especially in the rural portions of Oregon that historically have been dependent on surface resources such as timber and agriculture. The export of minerals also can provide additional economic stimulus to Oregon's port cities. The extent to which this mineral development may be achieved depends in part on the availability of high-quality geologic information that can be used to define areas favorable for the occurrence of a variety of valuable nonmetallic mineral deposits.

The nonrenewable nature of most mineral resources means that a variety of mineral resources should be identified in advance of need so that access for extraction can be provided by land-use planning processes. Commodity profiles such as this suggest opportunities for developing new resources, expanding existing operations, adding value to commodities by processing them in the state, and increasing the volume of resources exported to offshore markets.

SCOPE

This study was on a reconnaissance level because of the size of the state, limited time and money, and the large areal extent of tuffaceous units that could contain bentonite. Samples were taken primarily from roadside outcrops. Because of the reconnaissance nature of this report, only general conclusions should be drawn from it. More detailed sampling, including a properly structured drilling and testing program, is necessary before a specific deposit be characterized as having commercial possibilities.

ACKNOWLEDGMENTS

We are greatly in the debt of Dick Berg, Montana Bureau of Mines and Geology, for his generous advice on effective testing of bentonite. We appreciate the advice on sample preparation and testing and the sample testing provided by Glen Teague and Dave Leppert of Teague Mineral Products. For sample testing, samples of bentonite, and information on preparation and testing, we also thank Brad Hofland, Chris Glenn, and I. Edgar Odom of American Colloid Company and Donald Hentz of Federal Bentonite. Thanks are due to Bill Titus of the Geology Department of Portland State University for providing part of the X-ray diffraction (XRD) scans. Chuck Radasch, DOGAMI laboratory technician, performed most of the testing and the rest of the XRD scans. Ron Geitgey, DOGAMI industrial minerals geologist, interpreted XRD data. Gary Baxter, DOGAMI geochemist, performed the cation analyses. Dian Goldsmith typed the manuscript and the complicated data tables. Beverly Vogt and Klaus Neuendorf edited the manuscript and prepared the report for publication. Paul Staub and Mark Neuhaus prepared the maps and illustrations.

NATIONAL INDUSTRY STRUCTURE

INTRODUCTION

The U.S. Bureau of Mines collects and publishes mineral production and usage data and classifies clay into six groups: ball clay, bentonite, common clay and shale, fire clay, fuller's earth, and kaolin. The classifications are based on industrial usage and may reflect rock name, end use, or a physical property of the clay. Most fuller's earth is composed of Cabentonite; therefore, mineral statistics for both bentonite and fuller's earth were used in this study.

BENTONITE

According to Patterson and Murray (1983), the first shipment of bentonite for commercial purposes was made in 1888 from Rock Creek, Wyoming, by William Taylor, During 1986, according to the U.S. Bureau of Mines, bentonite was produced in 13 states. The 1986 output was 2.8 million tons, worth about \$91.4 million in value. Wyoming, Alabama and Mississippi, California, and Montana accounted for 56, 17, 9, and 6 percent, respectively, of the national total. Figure 1 shows the total domestic production of bentonite by end use for the period from 1963 to 1986. Production rose from 1.6 million tons in 1963 to 5 million tons in 1981 and declined to 2.8 million tons in 1986. Two trends have combined to lower the demand for bentonite. The first is the falling production of iron pellets in Michigan and Minnesota, and the second is a precipitous decline in oil and gas drilling. Bentonite, however, is being used in increasing amounts in civil engineering applications, including sealing sanitary land fills, sewage lagoons, and cyanide leach pads for heap leaching of gold ore.




Figure 1. Bentonite sold or used by domestic producers for specified uses from 1963 to 1986. Data from U.S. Bureau of Mines Minerals Yearbooks, Volume 1, 1963 to 1986.




Figure 2. Fuller's earth sold or used by domestic producers for specified uses from 1963 to 1986. Data from U.S. Bureau of Mines Minerals Yearbooks, Volume I, 1963 to 1986.

FULLER'S EARTH

According to Patterson and Murray (1983), there is some confusion about when and where the first commercial output of fuller's earth occurred. Small-scale mining of a clay, which was tested for use in refining of cottonseed oil, was reported in 1891 near Alexander, Arkansas. In 1893, a clay deposit containing the amphibolelike clay mineral attapulgite was recognized as fuller's earth near Quincy, Florida, and was developed two years later into a source of fuller's earth for the processing of mineral oil.

U.S. Bureau of Mines statistics show that during 1986 six states reported production of 1.9 million tons valued at \$125.5 million. Two states (Florida and Georgia) accounted for 52 percent of the total. Figure 2 shows twenty-three years (1963 to 1986) of production by end use. During these years, output climbed steadily from 0.5 million tons in 1963 to 1.9 million tons in 1986.

COMBINED STATISTICS

To provide a clearer picture of the total U.S. market for bentonite, the U.S. Bureau of Mines production statistics of Ca-bentonite produced as montmorillonite and sold as fuller's earth and the Ca-bentonite produced and sold as nonswelling bentonite were added together in this study to give the total Ca-bentonite production statistics in Table 1 (Plate 1). Total U.S. output of bentonite grew from 3.7 million short tons in 1975 to 5.7 million short tons in 1981 and decreased to 3.8 million short tons in 1986 (Figure 3). Cabentonite production averaged 25.6 percent of the total U.S.




Figure 3. Bentonite, including Ca-bentonite/fuller's earth sold or used by domestic producers for specified uses. Data from U.S. Bureau of Mines Minerals Yearbooks, Volume I, 1963 to 1986.

bentonite output for the period 1975 to 1981. As the output of Na-bentonite fell from 1982 to 1986, the production of Cabentonite rose to 34.4 percent.

USAGE

Drilling mud

For the last 12 years, drilling mud has been and should continue to be a major market for bentonite (Figure 1; Table 1, Plate 1). In the rotary drilling of oil and gas wells, bentonite is used in drilling mud to lubricate the bit, remove cuttings from the bit, and carry them to the surface. It also seals the wall of the hole, prevents drilling-fluid loss, and stops ingress of water from the rock being drilled. The gelling (thixotropic) property of high-swelling Na-bentonite stops cuttings from settling to the bottom of the hole and packing around the drill pipe and bit when the drill stem stops turning. If cuttings were allowed to pack the drill pipe and bit, the drill stem might be stuck to the point where it could not be turned or pulled out. Bentonite used in drilling muds must meet rigid standards set by the industry.

Iron-ore pelletizing

Taconite is cherty or jaspery iron ore that must be finely ground so that the iron-bearing minerals can be extracted. Because the fine dust cannot be used in a blast furnace, the iron-ore concentrate is pelletized by adding a small amount of bentonite to the taconite concentrate in a revolving drum or disk. In addition to its binding action, the bentonite absorbs water from the concentrate, thereby helping to dry it out.

In the past, the mining of taconite iron ore in Michigan and Minnesota provided a large steady market for bentonite. In recent years, however, the market for pelletized taconite has been declining. According to Kuck (1988), "Consumption of ore and agglomerates at U.S. iron and steel plants dropped to 55 million tons and was only slightly higher than that of 1982, making 1986 the second-worst year for U.S. ore producers since 1939." The mining of iron ore has been moving and will continue to move overseas. An organic binder (Carbinder Polymer 498), which has been developed by Union Carbide Corporation (Rosen, 1988), may be cheaper to use than bentonite and has a lower silica content.

Foundry sand binder

The foundry industry uses bentonite as a binder to hold the refractory sand particles together in a mold that then is filled with metal. The bentonite must be a mixture of non-swelling and swelling bentonite. The Ca-bentonite (nonswelling) gives high "green strength" (the mold holds together until water added to bentonite-sand mixture has evaporated), and Na-bentonite (swelling) gives high "dry strength" (the mold does not break when hot metal is poured into the mold).

The foundry industry seems to exhibit a more steady demand than the oil and gas industry. Specifications are high for this industry, but different users have slightly different specifications, and a producer must be able to meet those individual specifications to be successful in the marketplace.

Oil and grease absorbent and pet litter

The market for absorbent is growing. Major reasons may be the continuing urbanization of the nation and direct advertising to the nation's auto garages and pet owners. There are no formal specifications for this use; however, general characteristics must include high liquid and odor absorbency, no-dust quality, uniform granule size, and wet strength. The market is concentrated in population centers, and the product is often sold in 10-lb sacks. Lower grade bentonite can be used for this market, but by the time transportation and bagging are added, the product commands a high per-ton value.

Miscellaneous

The category labeled "Miscellaneous" in Figure 3 and Table 1 includes a wide variety of markets. There appears to be a relatively steady demand for these "miscellaneous" uses over time, although the individual markets included in the category change over time and are replaced by others.

A current growth market is for "environmental bentonite," used in civil engineering projects to seal sewage lagoons, sanitary land fills, and gold-ore leach pads. Bentonite is also used in sealing irrigation ditches, earthworks, and dams. Bentonite granules can be used to fill diamonddrill holes, seismic shot holes, and the interface between water-well casing and the ground to prevent pollution from moving into an aquifer. An additional civil engineering technique, called "slurry trench or slurry wall construction," used in digging trenches or walls (Gordon, 1983), which can be very costly and dangerous in unconsolidated earth. In this application, thick bentonite slurry is pumped into the trench as it is being dug. The bentonite keeps the walls of trenches from collapsing. Concrete is then poured into the bottom of the trench; as it fills the trench, the bentonite is drawn off. Alternatively, if a sewage pipe is laid at the bottom of the trench, the bentonite is recovered as the trench is backfilled.

Bentonite is also used as a carrier in horticultural sprays and insecticides, as a suspending agent, and as paste-former and an emulsifying agent for asphalts. It is used for clearing turbid water and for sewage purification. It is also added to concrete to improve workability and to aid in its placement.

EXPORTS

U.S. exports

Between 1982 and 1986, bentonite (not including fuller's earth) was shipped to 92 countries. The export value of the bentonite ranged from \$42.5 million to \$54.7 million (see Table 2). Exports to Canada and Japan accounted for an average of 29 and 18 percent, respectively, for this entire period. Table 1 shows tonnages and end use of the exports from 1975 to 1986. O'Driscoll (1988) summarized the worldwide status of bentonite in his July 1988 Industrial Minerals article, "Bentonite, Overcapacity In Need Of Markets."

Table 2. U.S. bentonite exports, by country and year (in thousands of dollars).*

Export country	1982	1983	1984	1985	1986	
Algeria Angola Argentina Australia Austria	\$ 65 199 140 2,666 3	\$ 0 11 899 0	\$ 0 124 37 2,738 0	\$ 0 49 1,179	\$ 0 52 84 1,277 30	
Bahrain Bangladesh Barbados Belgium/Luxembourg Belize		16 16 28 0	27 8 13 29 28	2 18 43 11	0 14 15 81 0	
Bermuda Bolivia Brazil Cameroon Canada	0 0 2,551 34 12,543	1,606 1,739	1,/44 5 14,507	2,0/1 0 16,280	2,09Z 0 12,459	
Chile China Colombia Congo Costa Rica	730 966 57 12	1,184 609 0	641 38 319 0 38	182 27 7/4 0 37	526 122 201 0 17	
Cyprus Czechoslovakia Dominican Republic Ecuador Egypt	0 2 4 247 185	10 10 217 310	0 10 230 197	0 21 136 813	0 0 24 143 190	
El Salvador Ethiopia Finland France Prench Pac. Island	37 0 14 262 Is 0	13 0 545	31 172 204 3	8 0 111	0 0 124	
Gabon Germany West Greece Gustemala Gusyana	900 5 457	1,832 1 31 0	256 679 0 134	158 873 205 1	127 4 14	
Haiti Honduras Hong Kong India Indonesia	24 234 33 24	55 340 46 828	11 189 27 5	10 210 38 705	118 37	
Iraq Ireland Israel Italy Ivory Coast	15 0 167 136 35	115 35	0 1 39 4 0	18 0 70 0	31 42 0	
Jamaica Japan Jordan Kenya Korea South	8,539 0 0 952	7,583 7,583 0 840	6,990 1 1,256	8,826 0 3	9,629 1 1,456	
Kuwait Lebanon Lee/Windward Isles Liberia Libya	1.578 0 0 0 0	647 6 1 0	0 67 67	27 0 0 116	278 0 11 0	
Madagascar Malaysia Maxico Neth. Antilles Netherlands	136 797 16 2,303	101 180 1,275	70 525 0 2,467	170 483 311 0 1,645	4,314 521 0 2,219	
New Zealand Nigeria Norway Pakistan Panama	50 38 275 93 37	34 2 2 20 19	89 12 464 370 14	22 118 218 27	87 0 197 24	
Papua New Grinea Paraguay Peru Philippines Poland	1,192 2,192 2	52 1 169 984 0	423 605 0	159 439 0	0 88 593 6	
Portugal Qatar Rep. of S. Africa Saudi Arabia Senegal	27 0 336 4,772 0	25 0 246 961 0	12 14 253 703 0	67 0 65 307	19 0 133 0 8	
Singapore Spain Suriname Sweden Switzerland	2,414 377 0 5 21	2,899 160 16 5 17	1,725 214 13 3	1,683 135 11 7	1,267 138 12 0 220	
Syria Taiwan Thailand Trinidad & Tobago Tunisia	897 385 145 64	1,410 451 153 8	1,784 625 210 0	1,788 550 204 0	2,007 320 132 0	
Turkey United Arab Emira United Kingdom Uruguay Venezuela	2,344 2,344 33 2,718	780 1,128 3 1,536	206 1,866 15 1,554	258 1,129 13 886	10 20 1,499 6 1,363	
Yemen (Sana) Yugoslavia Total	0 54,712	\$42,580	\$45,375	\$44,973	77 0 \$44,607	

⁸Data provided by International Trade Institute, Portland, Oregon, compiled from U.S. Department of Commerce statistics.

Pacific Northwest exports

Between 1983 and 1986, bentonite was shipped from the ports of Portland, Oregon, and Seattle, Washington (Table 3) to 24 of the 92 countries listed in Table 2. These two ports accounted for 73 percent of the nation's total of 0.3 million tons exported in 1983 but only 39 percent of the national total of 0.4 million tons exported in 1986. Table 3 shows that from three to eight times more bentonite was exported from Portland than from Seattle; however, the Seattle-exported material had a per-ton value twice as high as that being exported from Oregon.

In June 1988, when the pound sterling was floating at around 1.70-1.90 = £1.00, bentonite prices were as follows (Industrial Minerals, 1988):

Wyoming, foundry grade, 85 percent
<200 mesh, bagged, 10-ton lots
del. UK £120-130
FOB plants, Wyoming, rail hopper cars,
bulk, short ton\$28.60-30.50
FOB plants, Wyoming, bagged rail cars,
short ton
Fuller's earth, soda-ash-treated del.,
UK foundry grade, bagged
Civil engineering grade, bulk
Oil Companies Materials Assoc.,
bulk, del. UK
API, FOB plant, Wyoming, rail cars,
bagged, short ton\$44.00-45.50
The above prices suggest that, at that time, foundry-grade
bentonite was shipped from Seattle, while lower cost grades
and the state of t

were shipped from Portland.

Table 3. Pacific Northwest exports of bentonite. Values in short tons unless otherwise noted. Numbers do not in all cases add up to totals because of rounding and exports to unlisted countries.

Year		1983			1984			1985			1986			1987		
Port district	Portland	Seattle	Total	Portland	Seattle	Total	Portland	Seattle	Total	Portland	Seattle	Total	Portland	Seattle	Total	
Export country																
Australia	18,229	147	18,376	26,560	190	26,750	19,768	158	19,926	23,666	577	24,243	6,818	1,203	8,021	
Brazil	. 0	0	0	0	0	. 0	0	0	0	. 0	0	. 0	5,614	0	5,614	
Canada	0	7,948	7,948	0	7,108	7,108		2,776	2,776	. 0	2,259	2,259	0	3,683	3,683	
China	0	0	0	362	0	362	312	0	312	0	895	895	0	588	588	
France	12,478	0	12,478	0	0	0	0	0	0	0	0	0	0	0	0	
Hong Kong	4	2,411	2,415	0	521	521	210	100	310	0	139	139	. 0	418	418	
India	0	0	0	0	0	0		0	0	0 1	0	0	0	66	66	
Indonesia	20,647	19	20,666	0	0	0	14,081	0	14,081	0	0	0	0	311	311	
Japan	70,585	357	70,942	61,650	694	62,344	91,811	243	92,054	78,736	298	79,034	103,894	7,046	110,940	
Korea South	0	2,052	2,052	168	2,669	2,837	0	3,640	3,640	0	2,731	2,731	0	2,784	2,784	
Kuwait	13,459	0	13,459	0	0	0	7	0	7	8,871	0	8,871	0	0	0	
Malaysia	0	439	439	0	241	241	0	375	375	0	5	5	. 0	575	575	
Netherlands	6,891	0	6,891	. 0	0	0	0	0	. 0	0	0	0	0	168	168	
New Zealand	0	12	12	0	10	10	0	102	102	0	84	84	0	119	119	
Vorway	0	0	0	3,182	0	3,182	0	. 0	0	0	0	0	0	0	0	
Other Pacific isles	0	0	0	0	. 0	0	0	0	0	0	0		. 0	2	2	
not otherwise listed											, ,					
Peru	0	0	0	0	5	5	77	0	77	0	. 0	0	0	0	0	
Philippines	0	3,240	3,240	0	2,647	2,647	0	2,449	2,449	0	565	565	0	2,310	2,310	
Saudi Arabia	10,997	0	10,997	12,696	0	12,696	6,759	0	6,759	0	0	0	. 0	0	0	
Singapore	49,730	500	50,230	27,311	894	28,205	25,199	305	25,504	16,300	967	17,267	10,970	1,800	12,770	
Taiwan	1,266	8,173	9,439	59	13,230	13,289	1,699	12,168	13,867	260	16,580	16,840	0	18,782	18,782	
Thailand	0	2,167	2,167	0	0	0	57	4,564	4,621	0	1,885	1,885	0	3,182	3,182	
United Kingdom	1,796	0	1,796	2,074	4,859	6,933	0	0	0	0	0	0	0	0	0	
Venezuela	5,536	0	5,536	8,800	0	8,800	5,762	0	5,762	0	0	0	6,387	0	6,387	
Pacific Northwest total	211,618	27,465	239,083	142,862	33,068	175,930	165,742	26,880	192,622	127,833	26,985	154,818	133,683	43,037	176,720	
U.S. total	,		327,319 ²			395,208 ²			463,819 ²			394,164 ²			NA	
Pac. NW total % of U.S. total	1 -	,	73%			45%			42%			39%			NA	
Total value of Pacific NW	* 10 102	\$2.05 (\$12.070	*7 (70	A. 576	#10.0/0	to 100	# 2 007	\$10.F10	#7.055	** ***	#10.00F	* 0.000	# 5 001	Å10 E01	_
exports in thousands of dollars (f.a.s.)	\$10,123	\$3,256	\$13,379	\$7,672	\$4,576	\$12,248	\$9,492	\$3,027	\$12,519	\$7,955	\$3,030	\$10,985	\$8,300	\$5,231	\$13,531	
Average value per short ton of bentonite exported	\$48	\$119	\$56	\$54	\$138	\$70	\$57	\$113	\$65	\$62	\$112	\$71	\$62	\$122	\$77	

Data provided by International Trade Institute, Portland, Oregon,
U.S. Department of Commerce statistics.

See Table 1.

NA = Not available

f.a.s. = free alongside ship

OREGON INDUSTRY STRUCTURE

Oregon has two producers who mine and mill bentonite: Central Oregon Bentonite Company, Roberts Route, Box 500, Prineville, OR 97754; and Teague Mineral Products, Route 2, Box 35C, Adrian, OR 97901 (Figure 4). From 1958, when Oregon bentonite production started, until 1986, about 185,000 short tons were produced in the state and sold.




Figure 4. Oregon bentonite producers.

CENTRAL OREGON BENTONITE

During 1958, Lewis O. Weaver and other members of his family started producing bentonite under the name Central Oregon Bentonite Company from his ranch and nearby Bureau of Land Management (BLM) land that had been staked with mining claims. An 8- to 10-ton per hour mill and bagging plant was built in 1959. Central Oregon Bentonite Company has marketed its bentonite for cat litter, binder in making stock-feed pellets, ditch and pond sealant, pitch control in paper mills, fire retardant, oil-well drilling mud, and filler in insecticides and fungicides. The mill is located 70 road mi from the nearest railhead and 230 road mi from the Port of Portland.

The bentonite bed is mined from a 3- to 4-ft thick bed in the John Day Formation with a stripping ratio of less than 1:1. An unpublished report by Mason (1981) places mineable reserves at about 3 million tons.

TEAGUE MINERAL PRODUCTS

Teague Mineral Products (Figure 5) started producing bentonite in 1974. The office, milling-bagging plant, and bentonite-zeolite operation is located 1 mi south of Adrian next to a railroad and 1 mi from a siding. The mill, which processes 3 to 7 tons per hour, is 395 road mi from the Port of Portland. The bentonite deposits are located 20 mi south and east on Succor Creek (sample 111, Table 4, Plate 3; Plate 2).




Figure 5. Teague Mineral Products mill on banks of the Snake River at Adrian, Oregon. The mill is used for storing, grinding, sizing, and bagging bentonite and zeolite mined in several areas of southeastern Oregon. Photo shows stored raw bentonite in open shed on left, silos for storage of finished product at right center. Product from this plant is shipped bagged or in bulk, by rail or truck.

According to the firm's unpublished data, two different beds have been or are being mined. One bed, the "Main Bed," occurs in an older sequence of beds (Sucker Creek Formation of Miocene age), which strike generally north-south and dip approximately 18° to the west. Vertical faulting subparallel to the strike brings this bed to or near the surface at several locations across the basin and in adjacent basins to the east. Total mineable strike length on the "Main Bed" exceeds 8 mi in the Succor Creek Basin, as determined by outcrop exposures and drill-hole discoveries. The "Main Bed" averages approximately 20 ft thick. Presently, drilled reserves with a 1:1 or less stripping ratio are approximately 1.5 million tons.

The second bed is named "GB Bed" for the graben block zone in which the bentonite occurs. The GB bentonite occurs in a younger sequence of beds (Sucker Creek Formation) that unconformably overlies the older tilted sequence of the "Main Bed." It has a low dip angle, approximately 6° to the southwest. The bed is generally about 30 ft thick. Present drilled reserves with a stripping ratio of about 1:1 are approximately 1 million tons.

Bentonite from this operation has been marketed mainly for use as sealants for sewage lagoons, hazardous-waste sites, gold-ore cyanide leach pads, and drill holes. Other uses are cattle food supplement, water-well drilling mud, and slurry type of trench excavation. The success of the Teague operation is due in part to its laboratory, which provides for quality control of products, and to its applied research for new applications.

MINING AND MILLING OF BENTONITE

Oregon bentonite is produced by open-pit methods. Overburden is removed and stockpiled for later use in reclamation. A bentonite bed is mined in 3- to 4-in. lifts. A disk is used to shave and windrow the top few inches off the bentonite bed. The loosened bentonite is air dried for a day or two and may be windrowed again to allow more air drying.

After air drying, the bentonite is removed and loaded into trucks with a front-end loader or with a wheeled elevator and taken to the mill, where it is stored under cover. At the mill, it is fed into a primary crusher, slicer, or breaker unit. At this stage, it may be further dried in a rotary kiln and sent over a screen to produce granules for cat litter. The material may go from the dryer to a pulverizer (Raymond roller mill), where cyclone dust collectors extract the minus-200-mesh pulverized product.

From the screens and/or cyclone, the material is moved to storage silos. Small amounts of soda ash are added to the bentonite at the mine or at the mill to improve the swelling property of the bentonite. The product is marketed either in bulk form or in bags of sizes ranging from 2,000-lb supersacks to 10-lb cat-litter bags.

BENTONITE DEPOSIT MODELS

Bentonite deposits form in three different ways (Patterson and Murray, 1983). The first type of deposit—and most important from the commercial standpoint—forms from bedded air-fall volcanic ash or tuff that was deposited into a marine or alkaline-lake environment and subsequently altered to bentonite. Such lakes may or may not have been heated by hot springs. The most common parent volcanic material was andesitic to rhyolitic in composition.

The second type of deposit is a bedded sedimentary deposit in which the bentonite was not altered in place but rather eroded from a preexisting deposit, transported, and deposited into a lake.

A third way bentonite deposits form is by hydrothermal alteration. These bentonite deposits typically are not bedded

but occur in irregularly shaped bodies and grade into the host rock through partially altered zones. Fault zones, joints, and other areas of porosity that provide access for heated water control the shape of these bentonite deposits. Kaolinite and jasperoid may be associated with these bentonites.

Plate 2 shows the locations of several large basins ranging in age from 4 to 40 million years in eastern Oregon. During the time each of these basins was receiving sediments, major volcanic activity was occurring, giving rise to air-fall tuffs whose deposition, in turn, disrupted drainages and produced alkaline lakes. The basins trapped transported bentonite, and the volcanic centers produced heat and hydrothermal fluids that caused hydrothermal alteration.

SURVEYING OF OREGON BENTONITES

EXISTING DATA

A search of DOGAMI's Mined Land Reclamation program database for names of past and current bentonite producers revealed that Oregon has two. GeoRef and DOGAMI bibliographies and unpublished commodity and county files were checked for bentonite references. The BLM, the USDA Forest Service (USFS), and county geologists and road engineers were contacted personally by the authors for information on bentonitic areas.

The previously discussed bentonite deposit model of the volcanic ash fall into a basin was used as a guide for this study. Map explanations for the 1:500,000 U.S. Geological Survey (USGS) maps for the east half (Walker, 1977) and west half (Wells and Peck, 1961) of Oregon were used to select tuffaceous sedimentary rock units containing volcanic ash that could have been altered to bentonite clay. The outlines of these rock units were transferred onto a same-scale (1:500,000) base map (Plate 2) and were interpreted to represent basins mostly of Miocene age.

FIELD SURVEYING

The reconnaissance-level field survey included sampling of bentonite beds, mine stockpiles, and finished products of bentonite producers. In addition, roads crossing the identified sedimentary basins were driven for an estimated total of 25,000 mi. Roadcuts, excavations, and outcrops visible from the roads were examined for signs of swelling bentonite such as popcorn weathering (Figure 6; site 40, Plate 2), alligator-hide weathering (Figure 7; site 65, Plate 2), and unvegetated hillsides (Figure 8; sites 40-44, Plate 2). When a likely outcrop was found, a shallow trench was dug to below the popcorn or alligator hide, and a sample was taken (Figure 9; site 12, Plate 2). The sample site was marked on the 1:500,000-scale map and on a 1:24,000-scale map. A small amount of hand augering was done on a couple of outcrops (sites 42-44 and 135-140, Plate 2).




Figure 6. Bentonite outcrop at site 40 showing popcorn weathering (see Figure 8).

The area covered by this study was extremely large, and a decision was made to sample from locations with expandable soil characteristics. Expandable bentonite, therefore, was the main focus of the study.

All samples were collected by DOGAMI staff except for seven processed samples that were provided by the production firms. Included are two mill samples from Central Oregon Bentonite (samples 86 and 87), one mill sample from a zeolite producer (sample 89), two mill samples from Teague Mineral Products (samples 96 and 97), and one sample each from two Wyoming producers (samples 153 and 154).

OBSERVATIONS MADE DURING FIELD SUR-VEY AND LABORATORY WORK

During the study, the following observations were made: (1) The surface expression of a bentonite outcrop may appear different, depending on whether it is on the north side of a hill or on the south side of a hill. On the south side, the popcorn weathering seems to be thicker. (2) A siltstone with very little bentonite can produce a good popcorn surface. (3) On an outcrop, a 6-in. layer of bentonite can produce what appears to be a 4- to 5-ft bed of bentonite when the popcorn soil drapes down over an underlying unit. (4) Although field observations indicated no evidence of hydrothermal activity, laboratory analyses of samples 130 and 152 showed anomalous amounts of water-soluble lithium cations, indicating some hydrothermal activity. (5) Sample preparation methods and temperature and length of drying time affected water-loss analyses profoundly (Appendix 8).

COMPILATION GEOLOGIC MAP SHOWING SAMPLE LOCATIONS AND BASIN OUTLINES (PLATE 2)

Plate 2 shows the basin-defined tuffaceous units that were sampled for bentonite, sample locations, and the two producer mines and mills. All but seven samples are considered



Figure 7. Bentonite outcrop at site 65 showing alligator hide weathering.




Figure 8. Hand augering at sample site 40-44, which is a bentonite outcrop with unvegetated hillside. Figure 6 is a close-up of site 40.



Figure 9. Shallow sample trenching of bentonite outcrop at site 12.

to represent ash altered to bentonite in an alkaline lake environment.

Samples 133 through 140 appear to be hydrothermal in origin because of lack of bedding. Sample 46 may be transported material. Samples 5, 6, and 7 appear to be marine sediments with a shallow weathered zone of bentonitic clay.

The reconnaissance nature of this study determines the types of conclusions that can be made from it. For example, it is not known which geological basins or tuff units are most likely to contain commercial bentonite deposits. However, it is clear that a relationship exists between sampling density and geological basins. The sample density is more a function of visible bentonite occurrences than a lack of road coverage. An absence of sample sites does not mean that the area or basin does not contain bentonite. All it means is that in the course of this study the authors did not find any bentonite cropping out along the road in that particular area. Future detailed geologic mapping at a scale of 1:24,000 may show correlations between bentonite beds and specific tuff units that were not detectable at this reconnaissance level.

LABORATORY TESTING

SAMPLES

Of the 154 samples submitted to the laboratory, 147 were collected in the field, and five were mill-run samples from two Oregon Na-bentonite producers and one zeolite producer. Two additional mill-run samples of "Wyoming" bentonite obtained for comparison from two Wyoming producers (American Colloid Company [sample 153] and Federal Bentonite [sample 154]) were also analyzed.

TESTING RATIONALE

Sampling for this study was done to identify deposits of swelling bentonite (Na-bentonite). As field testing for swell was not done, the only sampling control in some cases was the lack of graininess typical of any clay, and it was inevitable that a number of nonswelling materials would be collected. Therefore, a preliminary laboratory test for swell was used to differentiate the swelling (Na-bentonite) and nonswelling (Ca-bentonite) samples. Swell tests with added soda ash were performed to determine which nonswelling samples could be "activated" (made to swell) and which low-swell samples would show improved swell.

Regis (1978) discusses the problems associated with the testing of bentonite, stating, "Testing of bentonite for its specific physical properties and use is hampered by the fact that there are no universally accepted specifications for the major uses. Specific tests for evaluating bentonite for a wide application of uses do not exist." Regis did suggest a testing procedure designed to identify high-grade bentonite, which he characterizes as "one which possesses unique properties which can be mined, processed and marketed for all of the major uses."

Samples were tested for only selected properties in this reconnaissance study. The primary purpose of the study was to identify deposits that had some potential use rather than to find "universal use" bentonite. To that end, samples were tested for a few physical properties that are commonly specified in a variety of applications. Strict adherence to the testing procedures specified by the American Petroleum Institute (API) for certain physical properties was not possible because of equipment limitations. Limited cation analysis was performed to better characterize the materials being tested.

The tests employed in this study included bulk X-ray diffraction (XRD), moisture content, swell (with and without soda-ash treatment), grit content, water loss (with and without soda-ash treatment), and water-soluble and exchangeable cation contents. All tests (other than XRD) were performed in the DOGAMI laboratory. American Colloid Company, Federal Bentonite, and Teague Mineral Products laboratories provided some quality-control data. The test methods are described in the Appendixes.

SAMPLE PREPARATION (PITFALLS)

Bentonite properties are extremely sensitive to the specific manners of sample preparation (see Appendix 8, Tables 12 and 13). Correct and documented preparation of bentonitic samples prior to general testing and correct preparation for certain types of tests are of critical importance. In the laboratory, bentonite becomes a fragile material unless knowledgeable care is exercised.

Three interrelated factors that can affect moisture content and/or particle characteristics and thereby affect physical properties of bentonite were identified: (1) exposure to "elevated" temperatures, (2) type of pulverizer employed, and (3) the mechanical action produced by a pulverizer or other equipment.

Drying at some step in sample preparation is a nearly universal practice. It is apparently done to make a sample more amenable to pulverizing and/or to lower the moisture content to some optimum range wherein the optimum physical properties are retained. (In industry, the latter factor coincides with the desire to reduce shipping weight and is a major production and quality-control problem.) As overdrying can adversely affect physical properties (Papke, 1970; Odom, 1986), the advice of several individuals (R. Berg, G. Teague, D. Leppert; personal communications, 1988) was followed, and samples were pulverized and tested in the airdried condition.

In similar studies (Berg, 1969; Papke, 1970), samples were uniformly pulverized to a desired particle size (e.g.,>90 percent <200 mesh). For a sample that is predominantly bentonitic in content, pulverizing to a very fine particle size should not be necessary; disaggregation upon water slurrying prior to testing should produce extremely fine particles. Pulverizing a less bentonitic sample poses a problem: how to reduce the more abundant concomitant minerals with naturally larger particle sizes to some smaller desired size without overheating the sample. As Berg points out, pulverizing with the wrong equipment can generate sufficient heat to adversely affect physical properties. On the advice of several consultants and producers, a Raymond mill was used in this study for sample pulverizing.

The factor labeled "mechanical action," which is (along with heat) a product of the pulverizer employed, is used here to account for the marked differences in physical properties observed with samples prepared in different types of pulverizers. Mechanical action apparently causes a change in particle characteristics, which, in turn, changes physical properties. This action is probably related to that found in extrusion (Odom, 1986) and compaction (Alther, 1983) processes that are used in industry to beneficiate bentonite. Mechanical action and (mechanically created) heat effects were expected to be minimal with the Raymond mill used in this study.

The requirements for a homogeneous sample for testing are evident. Subsamples of the prepared laboratory sample must be representative of that laboratory sample; the laboratory sample must be representative of the field sample; and the field sample should, in turn, be representative of the deposit.

Because of the effects of sample preparation on sample results, the Appendixes in this report must be consulted when using Table 4 (Plate 3), as the data must be used with the qualifications indicated.

QUALITY CONTROL

For this study, quality control consisted entirely of replicate testing for measurement of precision. Statements of the reproducibility of the various tests are given in the Appendixes. No well-characterized bentonite standard was available for measurement of accuracy.

RESULTS

OVERVIEW

Oregon produces commercial grades of bentonite. This study, which is a reconnaissance-level survey, is the first and only statewide sampling of bentonite occurrences. A sampling program with 152 samples is a very small survey for a state the size of Oregon. The heart of this study is the geological-basin outline and sample-location map (Plate 2) and the survey-data table (Table 4, Plate 3). Test results of samples collected from Oregon bentonite occurrences show that Oregon bentonite has physical properties similar to those of samples obtained from commercial producers.

SURVEY-DATA TABLE

The first ten columns of the survey-data table (Table 4, Plate 3) give location and field-site data corresponding to the locations plotted on the map (Plate 2). All of the columns except the sample-interval column are self-explanatory. In it, the intervals listed in the table are slope distances. If the sample was a vertical sample, it was taken from top to bottom of the bed. If a sample interval starts from any number but 0, it means that it was the next sample taken downslope from the previous sample. If there is a gap between the two samples, it means that there were two bentonite beds with a nonbentonite bed between them.

The rest of the table is devoted to results of laboratory testing. The testing included physical tests, mineral determination by X-ray diffraction, and chemical tests. After the test data were listed in Table 4 (Plate 3), the authors spent a great deal of time trying to find relationships between what was seen during field surveying and what was found with the physical tests, X-ray diffraction, and chemical tests. No obvious relationship was found. Others have also found these relationships hard to discover, including Rath (1986),

who stated, "Attempts to correlate physical and chemical properties of bentonite with rheologic properties have been mostly unsuccessful."

The market value of a bentonite source is due to its physical properties. The physical testing in this study indicated that the 18 samples treated, according to common industry practice, with soda ash that had 800 percent or higher swell should be considered Na-bentonite ("Wyoming"). The sixteen samples with 400- to 799-percent swell should be considered to be Na-Ca mixed bentonite, the 48 with 100- to 399-percent swell to be Ca/Na-mixed, and the rest with less than 99-percent swell to be Ca-bentonite, one of the other clay minerals, or a zeolite. The 46 samples that were soda-ash treated and had 10-ml water loss or less should be considered as having possible value for sealing purposes (Dirmeyer and Skinner, 1964).

The data in the grit section of Table 4 must be viewed with reservations. Much of the grit that was listed in the "Crushed" column was shown to be bentonite by the reduction in grit after milling. Another reason the grit percentages may be high is that the samples were not milled, as is called for in industry testing. Even with the above reservations, 17 samples out of a total of 44 milled showed less than 4 percent grit.

To characterize and determine the range of minerals in the grit fraction, 13 samples as received and two milled samples of the 13 were tested by X-ray diffraction. Table 5 shows the results of the X-ray diffraction analyses.

These three physical tests (swell, grit, and water loss) show that many of the deposits that were sampled warrant resampling, detailed mapping, and detailed testing for specific markets. The study results indicate that Oregon has bentonite resources that could meet a variety of end-use markets.

Table 5. X-ray diffraction results for grit.

2 tr	4 tr		32	32*	49		e nu					*		
			32	32*	49	57	E 0	0.0	00			*		
tr	tr	+~				٠,	56	86	89	93	94	94	117	139
		tr				m	m	tr	tr	М			tr	tr
tr	tr	tr	М	m	М	m	tr	М	m	M				M
						tr							tr	
			m	m				m	m		М	M	tr	
tr	tr	tr				tr								
tr	tr				m									
														m
	 tr			m tr tr tr	m m tr tr tr	m m tr tr tr	tr m m tr tr tr tr	tr m m tr tr tr tr tr	m m m tr tr tr tr	m m m m tr tr tr tr	m m m m tr tr tr tr	tr M tr tr tr tr	tr	tr tr m m m m M M tr tr tr tr tr

^{* =} Sample milled

M = Major

m = minor

tr = trace

FUTURE STUDIES

This study was designed to be reconnaissance, not definitive. Different approaches, assumptions, laboratory techniques, and laboratory tests would have produced a more nearly complete study. As identification of deposits of swelling bentonite was the first priority of this study, there were biases against collecting fuller's earth/Ca-bentonites and against testing them (where collected) for the properties needed in the fuller's earth market.

This study can be considered, instead, as a large pilot study. Future field studies should include the following: (1) detailed sampling and mapping of sample sites that showed high swell (Na-bentonite), with the sample taken over a long interval (such as was done at sites 15 [0-30 ft], 50 [0-7 ft], 57 [0-10 ft], 62 [0-5 ft], and 121 [0-10 ft]); (2) a rerun of the Cabentonites with swell less than 99 percent, as received and acidified for fuller's earth properties; (3) detailed sampling

and mapping of those Ca-bentonites; (4) implementation of a much more detailed sampling program in areas with existing detailed geologic mapping to see if correlations can be found between rock units and deposits, thereby making it possible to build a geological model for predicting the occurrence of bentonite resources; and (5) outcrop sampling to relate grade to depth.

Future laboratory studies should include the following: (1) testing for fuller's earth properties; (2) grit testing the rest of the milled samples; (3) running foundry sand binder tests for the Na/Ca-bentonites and Ca/Na-bentonites; (4) viscosity testing; (5) tests for colloid content; (6) pH; (7) gel strength; (8) cation exchange capacity; (9) water loss at reduced pressure (to emulate scalant use); and (10) more detailed mineralogy through XRD analysis.

REFERENCES

- Alther, G.R., 1983, Low-grade bentonites improved by chemical activation and compaction: Mining Engineering, v. 35, no. 9, p. 1312-1314.
- American Petroleum Institute, 1985a, API recommended practice. Standard procedure for field-testing drilling fluids, 11th ed.: Washington, D.C., American Petroleum Institute, API RP 13B, 20 p.
- ———1985b, API specification for oil-well drilling-fluid materials, 11th ed.: Washington, D.C., American Petroleum Institute, API Spec 13A, 28 p.
- Ampiam, S.G., 1985, Clays, in Mineral facts and problems: U.S. Bureau of Mines Bulletin 675, p. 157-169.
- Auer, D.L., and Thayer, R.L., 1978, Bentonite—update: Production, reserves, quality control, and testing: Salt Lake City, Utah, Society of Mining Engineers of AIME Preprint 78-B-59, 8 p.
- Baldwin, E.M., 1964, Geology of Oregon (2nd ed.): Eugene, Oreg., University of Oregon Cooperative Book Store, 165 p.
- Berg, R.B., 1969, Bentonite in Montana: Montana Bureau of Mines and Geology Bulletin 74, 34 p.
- Brown, C.E., and Thayer, T.P., 1966, Geologic map of the Canyon City quadrangle, northeastern Oregon: U.S. Geological Survey Miscellaneous Geologic Investigations Map I-447, scale
- Corcoran, R.E., Doak, R.A., Porter, P.W., Pritchett, F.I., and Privrasky, N.C., 1962, Geology of the Mitchell Butte quadrangle, Oregon: Oregon Department of Geology and Mineral Industries Geological Map Series GMS-2, scale 1:125,000.
- Dirmeyer, R.D., Jr., and Skinner, M.M., 1964, Evaluation of Colorado clays for sealing purposes: Fort Collins, Colo., Colorado State University Experiment Station, Civil Engineering Section, Technical Bulletin 83, 36 p.
- Evernden, J.F., and James, G.T., 1964, Potassium-argon dates and the Tertiary floras of North America: American Journal of Science, v. 262, no. 8, p. 945-974.
- Evernden, J.F., Savage, D.E., Curtis, G.H., and James, G.T., 1964, Potassium-argon dates and the Cenozoic mammalian chronology of North America: American Journal of Science, v. 262, no. 2, p. 145-198.
- Fleshman, H.G., 1987, Western sodium bentonite industry, 1980's and 1990's: Salt Lake City, Utah, Society of Mining Engineers of AIME Preprint 87-77, 4 p.
- Gordon, C., 1983, The slurry wall comes to Seattle: Pacific Builder and Engineer, v. 89, no. 15 (August 8), p. 21-24.
- Hampton, E.R., 1964, Geologic factors that control the occurrence and availability of ground water in the Fort Rock Basin, Lake County, Oregon: U.S. Geological Survey Professional Paper 383-B, 29 p.
- Hodge, E.T., 1932, Geological map of north-central Oregon: University of Oregon Publication, Geology Series, v. 1, no. 5, 7 p., scale 1:250,000.
- Industrial Minerals, 1988, Prices: Industrial Minerals, no. 249 (June 1988), p. 82-83.
- Kittleman, L.R., Green, A.R., Haddock, G.H., Hagood, A.R., Johnson, A.M., McMurray, J.M., Russell, R.G., and Weeden, D.A., 1967, Geologic map of the Owyhee region, Malheur County, Oregon: Eugene, Oreg., University of Oregon Museum of Natural History Bulletin 8, scale 1:125,000.
- Kittleman, L.R., Green, A.R., Hagood, A.R., Johnson, A.M., McMurray, J.M., Russell, R.G., and Weeden, D.A., 1965, Cenozoic stratigraphy of the Owyhee region, southeastern Oregon: Eugene, Oreg., University of Oregon Museum of Natural History Bulletin 1, 45 p.
- Klinefelter, T.A., and Hamlin, H.P., 1957, Syllabus of clay testing: U.S. Bureau of Mines Bulletin 565, 67 p.
- Kuck, P.H., 1988, Iron ore: U.S. Bureau of Mines Minerals Year-book 1986, v. I, p. 495-528.

- Leppert, D., 1985, Zeolites and bentonites: The entrepreneurial approach: Adrian, Oreg., Teague Mineral Products, paper presented at 91st annual convention, Northwest Mining Association, Spokane, Wash., 7 p.
- Malde, H.E., and Powers, H.A., 1962, Upper Cenozoic stratigraphy of western Snake River Plain, Idaho: Geological Society of America Bulletin, v. 73, no. 10, p. 1197-1219.
- Mason, R.S., 1981, Tonnage calculations, Central Oregon Bentonite Company claims, Crook County, Oregon: Unpublished report to Central Oregon Bentonite Co., on file at Oregon Department of Geology and Mineral Industries, 8 p.
- Merriam, J.C., 1901, A contribution to the geology of the John Day Basin, Oregon: University of California, Department of Geological Sciences Bulletin, v. 2, no. 9, p. 269-314.
- ——1910, Tertiary mammal beds of Virgin Valley and Thousand Creek in northwestern Nevada. Pt. 1, geologic history: University of California, Department of Geological Sciences Bulletin, v. 6, no. 2, p. 21-53.
- Miles, W.J., and Blair, R.E., 1983, Industrial minerals uses in the drilling industry: Mining Engineering, v. 83, no. 10, p. 1397-1400.
- Moll, W.F., 1986, Absorbent clays: Salt Lake City, Utah, Society of Mining Engineers of AIME Preprint 86-334, 9 p.
- Newcomb, R.C., 1958, Yonna Formation of the Klamath River basin, Oregon: Northwest Science, v. 32, no. 2, p. 41-48.
- ———1966, Lithology and eastward extension of the Dalles Formation, Oregon and Washington, in Geological Survey research 1966: U.S. Geological Survey Professional Paper 550-D, p. D59-D63.
- Odom, I.E., 1986, Na/Ca montmorillonite: Properties and uses: Salt Lake City, Utah, Society of Mining Engineers of AIME Preprint 86-369, 13 p.
- O'Driscoll, M., 1988, Bentonite. Overcapacity in need of markets: Industrial Minerals, no. 250 (July, 1988), p. 43-67.
- Palmer, A.R., 1983, The Decade of North American Geology 1983 geologic time scale: Geology, v. 11, no. 9, p. 503-504.
- Papke, K.G., 1970, Montmorillonite, bentonite, and Fuller's earth deposits in Nevada: Nevada Bureau of Mines Bulletin 76, 47 p.
- Patterson, S.H., and Murray, H.H., 1983, Clays, in Lefond, S.J., and others, eds., Industrial Minerals and Rocks (nonmetallics other than fuels), 5th ed.: Salt Lake City, Utah, Society of Mining Engineers of AIME, v. 1, p. 585-651.
- Engineers of AIME, v. 1, p. 585-651.

 Piper, A.M., Robinson, T.W., Jr., and Park, C.F., Jr., 1939, Geology and ground-water resources of the Harney Basin, Oregon: U.S. Geological Survey Water-Supply Paper 841, 189 p.
- Prostka, H.J., 1962, Geology of the Sparta quadrangle, Oregon: Oregon Department of Geology and Mineral Industries Geological Map Series GMS-1, scale 1:62,500.
- ——1967, Preliminary geologic map of the Durkee quadrangle, Oregon: Oregon Department of Geology and Mineral Industries Geological Map Series GMS-3, scale 1:62,500.
- Rath, D.L., 1986, Origin and characteristics of Wyoming bentonite deposits, in Roberts, S., ed., Metallic and nonmetallic deposits of Wyoming and adjacent areas, 1983 conference proceedings: Geological Survey of Wyoming Public Information Circular 25, p. 90 00
- Regis, A.J., 1978, Correlation between physical properties and exchangeable chemistry of bentonites from the western United States: U.S. Bureau of Land Management Technical Note 313, 56 p.
- Rosen, M.R., 1988, CARBINDER Polymer 498: A new organic binder for taconite ore: Salt Lake City, Utah, Society of Mining Engineers of AIME Preprint 88-47, 20 p.

Shotwell, J.A., 1956, Hemphillian mammalian assemblage from northeastern Oregon: Geological Society of America Bulletin, v.

67, no. 6, p. 717-738.

Shotwell, J.A., with contributions by Bowen, R.G., Gray, W.L., Gregory, D.C., Russell, D.E., and Taylor, D.W., 1963, The Juntura Basin--Studies in earth history and paleoecology: American Philosophical Society Transactions, v. 53, pt. 1, 77 p.

Smith, W.D., 1926, The southeastern lake province (Physical and economic geography of Oregon, chap. XI): University of Oregon

Commonwealth Review, v. 8, nos. 2-3, p. 199-253. Swanson, D.A., 1969, Reconnaissance geologic map of the east half of the Bend quadrangle, Crook, Wheeler, Jefferson, Wasco, and Deschutes Counties, Oregon: U.S. Geological Survey Mis-

cellaneous Geologic Investigations Map 1-568, scale 1:250,000. Swanson, D.A., and Robinson, P.T., 1968, Base of the John Day Formation in and near the Horse Heaven mining district, north-

- central Oregon, in Geological Survey research 1968: U.S. Geological Survey Professional Paper 600-D, p. D154-D161.
- U.S. Bureau of Mines, 1963-1986, Minerals Yearbooks: Washington, D.C., U.S. Government Printing Office.
 Walker, G.W., 1977, Geologic map of Oregon east of the 121st
- meridian: U.S. Geological Survey Miscellaneous Investigations Series Map I-902, scale 1:500,000.
- Wells, F.G., and Peck, D.L., 1961, Geologic map of Oregon west of the 121st meridian: U.S. Geological Survey Miscellaneous Geologic Investigations Map I-325, scale 1:500,000.
- Wolfbauer, C.A., 1977, Exchangeable cations in Cretaceous bentonites from Wyoming and Montana: U.S. Geological Survey Open-File Report 77-158, 48 p.
- Worrall, W.E., 1975, Clays and ceramic raw materials: New York, John Wiley and Sons, 203 p.

APPENDIXES

APPENDIX 1. SAMPLE PREPARATION

Because of recommendations from bentonite producers, a pulverizer was selected that would pulverize but not unduly heat an air-dried but "damp" sample without altering the moisture content. The Raymond mill, a hammer/screen mill equipped with a screen with 0.024-in.-diameter holes, was used to produce a powder of 100-percent <610 micron size. Three producer laboratories used the same or similar pulverizers.

Field samples were air dried in porous olefin bags under room conditions for a period of time ranging from several months to just under two years. Judging by the moisturecontent determinations, it appears that the samples retained sufficient moisture so that the tested-for properties were not adversely affected.

Each field sample was crushed in its entirety to minus ¼-in. mesh. The first 97 samples were further reduced by passing them through a BICO pulverizer with plates set with a ½-in. gap. Each crushed sample was split on a Jones-type

splitter to obtain a raw laboratory sample with a volume of about ½ to ¾ pint.

Each raw laboratory sample was then pulverized in the Raymond mill to produce the powdered laboratory sample. Sample-to-sample contamination was reduced by compressed-air cleaning of the hopper between samples. As the amount of a sample left within the mill was inconsequential in comparison to the 100 to 200 g of the subsequent sample, and as a small portion of this next sample was then milled and discarded, carryover contamination was considered to be negligible.

The powdered laboratory sample was homogenized by rolling on a rolling cloth. This procedure was difficult because of the bulk of the sample but appeared to be effective, as judged by the close correlation of replicate analyses for water-soluble cations. The action of the mill itself apparently did much of the homogenizing. Each powdered laboratory sample was stored in a waxed-paper pint container to await testing.

APPENDIX 2. X-RAY DIFFRACTION PROCEDURES AND INTERPRETATION

For identification of the major clay and nonclay minerals, about 10 g were split from each crushed sample for bulk X-ray diffraction (XRD) analysis. Each split was hand ground to approximately minus 100 mesh and placed in a side-loaded powder pack mount. The samples were scanned from 2° to 65° 2 theta at a rate of 2° 2 theta per minute on a General Electric diffractometer with nickel-filtered copper radiation. The bulk samples were run by W.S. Titus under the supervision of M.L. Cummings, Department of Geology, Portland State University. Because of the large number of samples collected and the initial lack of in-house facilities for separation and X-ray diffraction, only bulk samples were run. No attempt was made to more fully characterize the clay by expansion, heat treating, or preparing oriented samples. Table 4 (Plate 3) contains the bulk-sample XRD data.

The grit fraction (wet sieved, plus 230 mesh) of selected samples was analyzed in the Oregon Department of Geology

and Mineral Industries (DOGAMI) laboratory on a Philips diffractometer with nickel-filtered copper radiation. The samples were scanned from 2° to 55° 2 theta at 2° 2 theta per minute.

Peaks were used to identify minerals, and peak heights were used to estimate their relative concentrations. Because some of the samples contained large components of noncrystalline volcanic ash or poorly crystallized clay minerals, reported minerals may constitute only minor or trace amounts of the total sample. More exact determination of the amount of each mineral phase was precluded by the variable degree of crystallinity, the high potential for preferred orientation of the mounted samples, and the inherent difficulties in any X-ray diffraction method of obtaining quantitative measurements in samples with several mineral phases.

APPENDIX 3. MOISTURE CONTENT

Moisture content was determined to provide information on the degree of hydration of all samples prior to testing and to allow calculation of equivalent weights (as per API Specification 13A) (American Petroleum Institute, 1985b) of subsamples to be tested for water loss.

A 5-g portion of an air-dried, Raymond-milled sample was weighed and placed in a tared aluminum dish, dried at

105 °C to constant weight, and cooled to room temperature in a desiccator. The dish + dried sample were then reweighed, and the moisture was calculated as in API Specification 13A (American Petroleum Institute, 1985b). A trial test of 12 samples showed that 4 hours' time at temperature of 105 °C was sufficient to reach constant weight. This time was used for subsequent samples.

APPENDIX 4. SWELL (PERCENT EXPANSION)

Swell is a somewhat crude field test that has been "upgraded" to a laboratory test. As Auer and Thayer (1978) point out, "This test procedure is very sensitive to operator technique." They list the most critical variables as the following:

1. Rate of addition. (Longer addition time tends to pro-

duce higher swell values.)

2. Size of addition. (High swelling clays can form "gel bridges" in the graduate, greatly increasing settling time.) The additions must be very small and isolated from the walls of the graduate.

3. Operator judgment when reading the final sediment volume. (It was noted that in their report they spent two

hours to sprinkle a 2-g sample.)

Test trials in this study with a much shorter time interval showed that the use of test samples measured by volume gave results that could not be consistently reproduced. Replicate tests using samples measured by weight, if run back-to-back, gave excellent reproducibility. But weight-measured samples tested over several weeks gave results that varied from poor to good in reproducibility.

For this study, the change in volume was ratioed to the

test sample weight.

Calculation Percent expansion = $\frac{100 \text{ (final volume - initial volume)}}{5 \text{ c}}$

Correction for moisture content was not made. The initial volume was set at 8 ml and was determined by measuring and averaging the volume of three "typical" samples.

Method for determining swell without soda ash addition

1. Add weighed (nominal) 5.000-g sample (air-dried, Raymond-milled) slowly to a 100-ml graduate containing 100 ml of distilled water. Let each small addition of sample

become wetted and sink before adding more sample.

Age 24 hours and then read volume of sample to nearest milliliter.

Method for determining swell with soda ash addition

After swell test in distilled water:

1. Pour off most of the water, retaining as much of sample

as is possible in the graduate.

- 2. With a stream of the soda ash solution (0.25 percent wt./vol. in water, anhydrous sodium carbonate, reagent grade) in a plastic wash bottle, stir up the sample in the bottom of the graduate. Stir the slurry with a stainless-steel spatula.
 - 3. Fill to 50-ml mark with the soda ash solution.
- 4. Let set overnight and read volume of sample to nearest milliliter. The soda ash solution provided, with respect to the 5-g sample, the equivalent of approximately 19 meq of sodium cation per 100 g of sample. The maximum swell that could be measured under these conditions was 840 percent, which proved to be inadequate for many samples.

Quality-control replicates

Two or more replicate swell tests were performed on 34 samples without and 25 samples with added soda ash solution. The reproducibility ranged from poor to good.

Comments

While swell testing will distinguish between swelling and nonswelling bentonites, the data herein should not be used for absolute statements of swell capability. The vagaries of the test method dictate caution. The less rigorous swell tests with added soda ash require greater caution. As soda ash addition is an industry practice, these data do provide a rough measure of the potential of the Oregon bentonites.

APPENDIX 5. GRIT

A preliminary wet-screen test for grit content of all the samples was performed on the air-dried, as-crushed splits. Selected samples were subsequently wet-screen tested for grit on dried (at 105 °C) Raymond-milled splits. The method for the milled samples follows that of Berg (1969, p. 10) rather than the more stringent method in API Specification 13A (American Petroleum Institute, 1985b). Both sets of data are reported in Table 4 (Plate 3).

Method for grit on as-crushed samples

- 1. Place an approximately 5-g sample in a stainless steel mixer cup and add about 0.02 g of Na₃PO₄ · 12H₂O.
- Add about 200 ml of hot tap water and stir for about 5 minutes on the Hamilton Beach mixer.
- Swirl the slurry and pour onto a 230-mesh (63-micron) stainless steel sieve.
 - 4. Wash screen with copious amounts of hot water.
- 5. Estimate the amount of the grit retained on the screen. If the grit was approximately 10 percent or less (by weight) of the original sample, a subsequent test of the sample in the milled form was performed. Where the sample slurry would not wash well because of gel formation and where the grit content appeared to be low (by feel), a test on the sample in milled form was performed. Otherwise, all samples with a water loss of 20 ml or less (in distilled water) were tested in the milled form for grit.

Method for grit on milled samples

- 1. Dry a nominal 20-g sample overnight or at least 8 hours at 105 °C.
- 2. Weigh the dried sample to three places after the decimal and transfer to a stainless steel mixer cup; add about 200 ml of hot tap water and 0.02 g of $Na_3PO_4 \cdot 12H_2O$ to the cup.
- 3. Mix for about 30 minutes. Watch for temperature buildup on mixer motors.

- 4. Let set for a minimum of 12 hours to age.
- 5. After aging, remix for 5 minutes and then pour slurry onto 230-mesh stainless steel sieve.
- 6. If any material remains in the bottom of the cup, add some water, mix, and add to material on the screen.
- 7. Wash thoroughly with the Gilson triple-head, conicalpattern sprayer to remove all of the undersize material.
- 8. Transfer the oversize to an aluminum dish, dry, and weigh.

Calculation

Percent grit = $\frac{\text{(weight > 230-mesh fraction)}}{\text{dry sample weight}}$

Ouality-control replicates

The reproducibility for grit was adequate; ten samples were tested in replicate (Table 6).

Comments

Grit is a specification applicable to a commercially produced bentonite: a milled product that is largely minus 200 mesh (dry screen). Wet screening of a minus ¼-in. mesh product, as was done for all samples in this study, is effective for measuring grit only in samples that disaggregate readily. Wet screening of selected Raymond-milled samples employed US 230-mesh (63-micron) sieves instead of the US 200-mesh (74-micron) sieves specified by API Specification 13A (American Petroleum Institute, 1985b).

Because of the emphasis on swelling bentonites in this study, it is likely that a number of nonswelling bentonites with low grit and of potential use were overlooked because one criterion (water loss) limited the number of the milled samples to be tested.

Table 6. Replicate grit analyses.

Map sample no.	- 1:	
	Grit - as crushed (%)	Grit - milled (%)
37	1.80, 1.72	
61	8.49, 6.69	3.15, 3.21
72	2.96, 2.85	, ,
73	1.73, 0.97	, * <u></u>
94	5.92, 6.02	
111	0.52, 0.45	, ,
117	0.96, 1.77	
127	<0.01, 0.09	
130	21.44, 22.60	
153		3.18, 3.22

APPENDIX 6. WATER LOSS

A modified form of the API Specification 13A (American Petroleum Institute, 1985b) method for water loss, or "filtrate of suspension" (API designation), was used. The major differences were the mixer employed (13,000 rpm vs. 11,000 rpm, as specified), the mixer impeller, and the mixing times that were limited in this study because of motor overheating). These factors had a major consequence on the accuracy of the data developed (see "Comments" below). Two Baroid filter presses were used.

The samples were tested in distilled water, both with and without added soda ash (anhydrous sodium carbonate, reagent grade). The soda ash provided, with respect to the 22.5-g test sample, the equivalent of 70 meq of sodium cation per 100 g of sample.

Method for water loss

1. For each sample, weigh duplicate 22.5 ± 0.01 -g samples (or the weight equivalent to 22.5 g at 10 percent moisture for samples with > 10 percent moisture). Place each in a 1-quart canning jar. About 10 samples in duplicate can be prepared at one time for testing on the next day.

Calculation of equivalent weight

Equivalent weight of sample =
$$\frac{20.25 \text{ g}}{(100\% - \%\text{H}_2\text{O}) \times 0.01}$$

NOTE: If the moisture content of the clay (as received) exceeds 10 percent by weight, use a weight of clay that is equivalent to 22.5 g with 10 percent moisture (American Petroleum Institute, 1985b, p. 14). A 22.5-g sample with 10 percent moisture contains 2.25 g water and 20.25 g bentonite.

2. Place a jar with sample on the top-loading electronic balance, zero, and add 350.00 ± 0.25 g of distilled water (or soda ash solution).

Table 7. Replicate water-loss analyses.*

Map sample n	Untreate A	d water B	loss	(ml C)	Treated A	water B	loss	(ml)	
10	33.0	32.0								_
15	11.5	12.0				8.5	9.	0		-
16	12.5	15.0	13	2.5		8.5	10.	5	9.	. 5
21	10.0	16.0								-
32	20.5	26.0								
37	73.5	87.0								
50	12.0	11.5								-
56	40.0	39.0								-
61	10.0	9.5								
65	33.0	40.0								
72	75.0	75.0								
73	57.0	82.0								-
94	33.0	35.0								
102	43.0	39.0				13.0	13.5	5		-
103	22.5	26.5				11.5	13.0	0		
104	35.0(?)	25.0				10.5	10.0	0		
107	17.5	19.0								-
111	8.5	8.0								-
117	17.5	19.0								-
127	12.0	12.5								-
130	9.5	12.0	12	2.5						
145	TE	TE				TE	13.5	5		-
151	9.5	9.0								-

^{*}Additional replicates given in Table 12. TE = Totally expelled: >350 ml

Cap the jar with the canning lid and shake by hand until the sample is thoroughly wetted.

4. Let age for a minimum of 16 hours. Trial tests indicate longer aging is not detrimental.

5. After aging, mix the duplicates of a sample for 5 minutes using Hamilton Beach Mixer immediately prior to testing.

Pour each slurry into a separate clean and dry test cell
with new filter installed and cap. Make sure the cells are not
leaking. Make sure the relief valves are closed and a dry
graduate is in place.

7. For the first test sample, simultaneously start the stopwatch and open the valve to admit the compressed air. Check to make sure the pressure is at 100 psi. After an interval, start the second test sample in the same manner.

8. After 7.5 minutes, quickly remove the graduate, collecting any liquid adhering to the collection tube, and replace with a dry graduate. Continue to collect the filtrate. Read the 7.5-minute volume to the nearest 0.5 ml and record.

9. At the end of 30 minutes, quickly remove the graduate, collecting any liquid adhering to the collection tube. Close the compressed air valve and open the relief valve. The second test sample is carried through the same series of steps.

10. Read the 7.5- to 30-minute filtrate volume to the nearest 0.5 ml and record. The filtrate volume collected during the 23.5-minute period is the volume reported in Table 4 (Plate 3). The API term for this volume is "filtrate-related 30 minutes."

Quality control

The reproducibility for water loss was generally good. Replicate data are given in Table 7. Table 8 provides a comparison of DOGAMI's data with that of other laboratories.

Comments

A comparison of the water-loss data from four laboratories—apparently obtained in strict adherence to the API method—with DOGAMI data indicates that the latter are significantly lower. DOGAMI data for water loss should be multiplied by 1.9 to obtain results that are comparable to API results (see Table 9).

The apparent cause is the 2,000 greater revolutions per minute (rpm) (versus that of the specified mixer) of the DOGAMI mixer and/or mixer impeller used in this study. The greater mechanical action caused an apparent beneficiation as far as water loss is concerned. However, as DOGAMI tested all of the samples and established that the precision of these results was good, the data are included in Table 4 (Plate 3).

Table 8. Interlaboratory comparisons of water loss.*

Map sample	AC	FB	T	A-1	A-2	DOGAMI	Map sample	AC	, FB	т	A-1	A-2	DOGAMI	
no.					,		no.							
10				77	60	33	81	,			96	147	29	
11				112	85	57.5	86	23	21			20	11	
12	47		44	113	35	20	90				93	64	42	
13				50	42	22.5	91		,		43.5	90	39	
14				78		32,33,30.5	92	'			55	28	17.5	
15		23		71	22	12	93	, '			103		22.5	
16	25			32	24	12.5,15	94				84	78	33	
17			56	130		31	99				80		33.5	
19				98		31	101	"		72	137		34.5	
20		32	34	34	26	13	102				65	66	41	
21				40	32	17	103		7,		48	46	24.5	
22				55	35	18	104	51		56	50	39	30	
23				31	23	12.5	105				71		77	
26			92	200		88	108				65		75	
28				86		59	109			90.5	72	/	79	
29				39		16.5	112			· · · · · · · · · · · · · · · · · · ·	88	16	7	
30			1_1_	88	1_	40	113				77	70	35	
31				38	, , , , , , , , , , , , , , , , , , ,	10	114			134	75	104	52	
32				53	46	20.5	116				155	26	14.5	
34			50	89		82	117		40	42	75	33	17.5,19	
36		, <u>. </u>	١	98		88	118	<u>, ,</u> ,	,	1 1 1	93	20	11	
37		·	124	99		73.5	120				49	34	18	
38			124	97	72,75	47	121	47		50	38	42	20	
39						88	122				22		14.5	
40	80			126	06,112	49	123				100	21	12.5	
40	80			120		47	123				100	21	12.5	
41				138		53	124				25		10	
42					102	49	125	31			25	30	14.5	
43					50	36	126				29	30	15.5	
44					57,60	41	127				72	23	12	
45		63	46	75	39	27	128				69	25	10	
47				75		47	129				86		. 9	
49				43		23	130		30		160	22	12.5	
50	27			24	44	12,11.5	132		86		32	73	49	
54 55	'		188	38 60		95 15	141 142			 71	65 114		44 82.5	
							=							
56				33		40	145			142	200	292	>200	
57					32,30	20	147				31	24	10	
58					23,21	14.5	148			240	250		TE	
60 61				80	16,18	10 10	150 151		135		130 39	21	62 9.5	
01					10,18	10	131			,	39	21	9.0	
62				125	38,38	24.5								
65			67	135		33								
73					114	57								
74			250	160		118								

^{*}Laboratory and its sample preparation prior to water-loss testing:

1 AC = American Colloid. Tested air-dried, minus 1/8-inch mesh samples as prepared in DOGAMI lab.

2 FB = Federal Bentonite. Same as above.

³ T = Teague Mineral Products. Air-dried, Raymond-milled sample, 100 percent <610 microns.</p>

A-1 = Lab A (Preparation method #1). Dried sample at 66 °C for 16 hrs and then pulverized in a BICO disc pulverizer.

A-2 = Lab A (Preparation method #2). Tested air-dried, Raymond-milled sample, 100 percent <610 microns.

TE = Totally expelled.

Table 9. Summary of ratios of individual laboratory results with respect to the corresponding DOGAMI results.

Laboratory	Ratio average ²	No. of samples	Ratio range	
AC	2.04	8	1.70- 2.35	
FB	2.15	8	1.76- 2.46	
T	1.83	18	0.61- 2.62	
Lab A-1 ³	3.26	75	0.40-12.80	
Lab A-2	1.89	57	1.20- 5.07	

 $^{^{1}}$ See footnote to Table 8 for identification of laboratories.

Limited trial testing indicated that water loss of some bentonites may be adversely affected by extended drying at the relatively low temperature of 66 $^{\circ}$ C. While not confirmed, the effect appeared to be limited to some, but not all, samples with Ca or Ca + Mg as the predominant cation(s).

² Average of ratio averages (AC, FB, T, and A-2) = 1.9.

³ The Laboratory A-1 results were considered to be unreliable. Two factors in Laboratory A's sample preparation method, drying and pulverizer employed, apparently altered the water-loss properties of most of the samples tested. This same laboratory, when testing samples prepared by the DOGAMI laboratory, produced results (A-2) that closely corresponded to the other results (AC, FB, and T). Berg's (1969) warning on the use of a disc-type pulverizer was not heeded by Laboratory A.

APPENDIX 7. CATION ANALYSIS

The cation extraction methods of Wolfbauer (1977) were modified for use in this study. The process consists of "washing" the samples to remove the water-soluble cations (WSC) and then extracting the exchangeable cations (EC) from the washed samples. The water-soluble cations and the exchangeable cations—of Na, Ca, Mg, K, and Li in both cases—were determined. The SO₄ ion, suspected by Wolfbauer to be the water-soluble constituent contributed by gypsum (common in many bentonites), was not determined. The cation exchange capacity (CEC) of the samples was not determined. However, the sum of the individual exchangeable cations (Regis, 1978) can be used as an approximate measure of cation exchange capacity; this summation is included in Table 4 (Plate 3). Determination of the cation contents was accomplished as indicated below.

ATOMIC ABSORPTION (AA) AND EMISSION ANALYSES

General information

Two sets of artificial standards and a reagent blank, one set for WSC and one for EC, were prepared for analysis of the samples. Aliquots of the 1,000-ppm cation solutions (99.999 percent purity) were made by weight to 0.0001 g on an electronic balance. The concentrations of the cations were calculated in terms of milliequivalents of cation per 100 g of sample (with respect to sample weight [0.5 g] in final analytical sample volumes) for instrument calibration. The standards and blanks contained La for WSC and La + acids + BaCl₂ for EC in order to match the matrix solutions of the samples.

Prior to analysis, the absorption or emission readings of the standards were obtained. For each cation, a reading vs. concentration curve was plotted to determine linearity and off-curve standards. Choice of the "high" standard (falling on the linear portion of a curve) was made, and this standard was used for blank/single-standard curve calibration. The reagent blank was used to zero the instrument. Corrections for contamination arising in the extraction, drying, and other steps were obtained from the "reagent + process" blanks and were applied to the data where warranted.

As these cations have few analytical lines, burner size (5 cm or 10 cm) and burner orientation with respect to optical path were the only parameters available for bringing sample absorbence/emission readings within the linear range. Dilutions of sample solutions were made where necessary. For each cation, three sequential, 2-second integrations were made. The Perkin-Elmer Model 4000 spectrometer used in this study provided automatic calculations of the average and coefficient of variation. A printer provided a permanent record of the data.

The instrument parameters used for both water soluble and exchangeable cation analysis are listed below. The flame used in all cases was air-acetylene.

Atomic absorption analyses

Na	Ca	Mg	K
589.0 nm	422.7 nm	285.2 nm	766.5 nm
Na HCL	Ca/Mg HCL	Ca/Mg HCL	Na/K HCL
0.7-nm slit	0.7-nm slit	0.7-nm slit	0.7-nm slit

HCL = Hollow cathode lamp

Emission analyses

-	Li	
Ş.	670.8 nm 0.2-nm slit	1.5

Method for water-soluble cations (0.5 g / 50 ml)—extraction and preparation for analysis

1. Weigh 0.5000 ± 0.0001 g of air-dried, Raymond-milled sample and transfer to a 50-ml "Falcon"-type plastic centrifuge tube.

2. Add via dispenser 25 ml of distilled water, cap the tube, and vortex until sample is thoroughly wetted.

3. Shake for 10 minutes (tubes in vertical position, shaking in horizontal direction.)

4. Centrifuge for 10 minutes at maximum rpm (3,400 rpm = 2,430 relative centrifugal force [RCF]).

5. Uncap the tube and very carefully decant the liquid onto a #42 Whatman filter/funnel assembly. Catch filtrate in a 100-ml plastic Tri-pour beaker.

6. Repeat steps 2 through 5 TWO more times. (Reserve filter paper and sample in the centrifuge tube.)

7. Reduce the filtrate volume to 30-40 ml (do not take to dryness) by heating at 105 °C in the horizontal air flow oven. Remove and cool to room temperature.

8. Transfer the reduced volume filtrate to a clean 50-ml "Falcon" centrifuge tube. Rinse beaker once with distilled water and add washings to tube.

9. Add via dispenser 5 ml of 10,000 ppm La solution (99.999 percent purity, in 0.3M HCl) for ionization suppression. Final concentration in sample is 1,000 ppm).

10. Carefully make to 50-ml volume with distilled water. Cap and store for analysis. Centrifuge those samples that have carry-over colloids.

A distilled water blank (one for every 20 samples) was carried through all of these steps; this blank was called the "reagent + process" blank.

Method for exchangeable cations (0.5 g / 100 ml)—extraction and preparation for analysis

- 1. Add 25 ml of the BaCl₂/alcohol extractant to the residue remaining from the water washing (for water soluble cations). Cap and vortex to disperse the residue.
 - Shake for 10 minutes.
 - 3. Centrifuge for 10 minutes at maximum rpm.
- 4. Carefully decant the liquid onto the same filter (in a funnel) used for the water soluble cation filtration. Catch the liquid in a 100-ml Tri-pour plastic beaker.
 - 5. Repeat steps 2 through 4 TWO more times.
- 6. In the moving air stream of a fume hood, reduce the alcoholic content of the liquid to a barely perceptible level (to reduce the flammability).
- 7. Take the barely alcoholic liquid to dryness at 105 °C in the oven. Remove the beaker and cool to room temperature.
- 8. Place the beaker with its dried residue on the top-loading electronic balance, zero, and add 100 ± 0.20 g of the acid extractant.
- 9. Cover the beaker and let set overnight to dissolve the residue.

10. Transfer 50 ml of the resultant solution to a clean 50ml "Falcon" tube, cap, and store for analysis. The excess solution is discarded.

A BaCl₂/alcohol blank called the "reagent + process" blank (one for every 20 samples) was carried through all of

BaCl₂/alcohol extractant — 0.1N BaCl₂ in 68 percent alcohol: Dissolve 12.214 g of reagent grade BaCl₂ · 2H₂O in about 200 ml of distilled water in a one-liter volumetric flask. Add 680 ml of ethyl alcohol and then make to volume with distilled water.

Acid extractant: Add 50 ml HCl + 25 ml HNO₃ + 50 ml La solution (1 percent La in 0.3M HNO₃) to a one-liter volumetric flask. Add distilled water to make to volume. (Reagent-grade chemicals used; final La concentration is 500 ppm).

Quality-control replicates

Duplicates of one in ten samples were extracted and analyzed for water-soluble and exchangeable cations. The data showed good reproducibility for the former and fair to good for the latter (see Tables 10 and 11).

Comments

The available centrifuge could not produce the 4,500-7,500 RCF used in the study cited. In decanting the water from some samples, small amounts of still-suspended colloids were carried over through the filter into the solutions for water-soluble cations. The approximately 0.03M HCl from the La solution is likely to have "digested" some of the exchangeable cations in the carried-over colloids. The result would be slightly higher than actual values reported for water-soluble cations in some samples. For the same reason, there would be less material remaining for extraction by BaCl₂/alcohol, and the results for exchangeable cations are likely to be somewhat lower than actual for some samples. Although the magnitudes of the errors in both cases are not known, they are believed to be small for all but a few samples, and the data reported are considered to be usable.

In the analysis for exchangeable Li, Li was <0.10 meg/100 g for all samples and was not included in Table 10. As indicated above, corrections to cation data for contamination arising from "reagent + process" blanks were made, and the corrected values were reported in Table 10. The corrections are given below. The minus sign indicated the

direction of the correction.

Corrections for "reagent + process" blanks

Water-soluble cation analyses:

Na -0.08 meq/100 g (<6 meq/100 g)

Na -0.22 meq/100 g (>6 meq/100 g, dilutions)

Ca None

Mg None

None

Li None

2. Exchangeable cation analyses:

Na -0.16 meq/100 g

Ca -0.15 meq/100 g

Mg -0.04 meq/100 g

-0.03 mcq/100 g

Table 10. Replicate cation analyses.*

.*	Water	-solubl	e catio	ns (mil	liequi	valents	/100 gr	ams)		Exchange	able cat	ions (mi	lliequiva	lents/10	0 grams)	
Мар	Na	ı	Ca	ı	M	g	K		. Na	a	· · · C	a	Mg		K	, ,
no.	A	В	A :	В	A	, B	A	В	A	В	. A	B	A 1 A 1	B		R
. 11	4.08	4.05	2.94	2.7	1.35	1.25	0.61	0.54	0.90	0.60	27.67	22.14	11.04	9.22	0.40	0.28
13	5.40	5.44	2.29	1.31	0.91	0.81	0.59	0.51					,	· ,		
17	9.5	10.2	4.5	4.5	1.39	1.54	0.41	0.41	7.95	9.09	12.61	15.75	1.38	1.54	0.16	0.28
65	1.08	1.00	0.82	0.83	0.38	0.38	0.09	0.08	0.10	0.11	8.90	9.76	3.64	4.01	0.11	0.05
67	8.8	9.4	6.7	7.5	2.22	2.43	1.04	1.12	2.74	2.68	31.32	29.13	7.70	7.48	0.91	0.84
69	0.2	0.2	0.24	0.22	0.07	0.07	0.34	0.32	0.13	0.06	4.28	3.65	0.99	0.82	0.62	0.44
86	27.9	27.5	7.7	7.5	1.25	1.98	0.20	0.18	53.34	53.79	6.45	5.47	0.40	0.50	0.31	0.35
93	19.2	17.9	7.7	7.2	2.62	2.55	0.43	0.40	7.87	7.75	17.39	17.54	5.06	5.19	0.26	0.26
108	3.66	3.66	10.2	9.9	4.27	4.25	0.21	0.20	0.11	0.19	4.42	5.69	1.70	2.26	0.21	0.31
113	38.0	37.0	74.6	81.2	2.46	2.50	1.43	1.45	1.62	1.86	31.12	36.90	0.87	1.08	0.15	0.20
115	1.85	1.79	0.16	0.16	0.29	0.27	0.16	0.13	5.36	5.06	16.07	14.78	8.42	7.84	1.60	1.40
126	21.8	21.5	4.9	5.3	1.58	1.96	1.59	1.64	10.53	10.09	13.53	12.64	3.72	3.53	1.33	1.15
136	1.08	0.99	0.49	0.47	0.20	0.19	0.12	0.13	0.47	0.57	10.06	9.56	3.62	3.42	0.91	0.36
152	5.18	5.19	10.6	10.2	3.03	2.91	0.59	0.54	0.76	0.69	13.37	13.76	3.40	3.47	0.91	0.85
154	13.7	14.5	3.10	2.90	1.99	1.89	0.20	0.20	38.06	35.20	15.69	13.06	7.57	6.53	0.93	0.86

^{*}A and B values are separate analyses on separate subsamples. Replicate analyses for Li, in both water-soluble and exchangeable forms, were all within the range of <0.01 to 0.01 meq/100 g and are therefore not included in this table.

Table 11. Cation analysis comparison.*

Map sample no.	Total	cation	content	(WSC +	EC)	(millequi	valent	s/100 grams)
	Na	DOG. Ca	AMI Mg	Total	Na	Americar Ca	Collo Mg	id Total
12	0.7	22.3	13.6	36.6	1	42	28	71
16	30.8	34.7	9.4	74.9	28	26	6	60
40	14.5	14.3	12.3	41.1	13	21	16	50
50	11.1	35.1	12.8	59.2	9	46	16	71
86	81.1	15.1	2.1	98.3	68	<1	<1	68
104	4.9	42.2	12.5	59.6	5	46	12	63
121	57.2	36.5	5.2	98.9	57	35	4	96
125	43.5	28.2	1.5	73.2	42	33	1	76
153	54.6	15.8	8.1	78.5	73	16	1 1	90

^{*}These results may not be directly comparable. DOGAMI used milled and homogenized samples. American Colloid used subsamples of as-crushed (minus 1/4-in.-mesh) samples that were not homogenized. Sample 153 was a milled sample provided by American Colloid. American Colloid's method extracts both water-soluble cations and exchangeable cations. Five grams of sample are treated with 50 ml of a 3.6-percent solution of benzyl trimethyl ammonium chloride in water. The Na, Ca, and Mg cations are exchanged with ammonium cations.

APPENDIX 8. TRIAL TESTS

Table 12. Effect of sample-preparation method and drying on water loss.*

Preparation method	Drying		Wate	er loss (ml)		Water los	s, Na trea	ted (ml)	As-tested moisture content (%)
A Air-dried, Raymond-milled, 100% <610 microns	None	32.0	33.0	30.5			8.5	9.0	9.0	10.81
Air-dried, Raymond-milled, 100% <610 microns	16 hours @ 66 °C	36.0	38.0	35.0						2.7
Air-dried, Angstrom mill, dry- milled to 100% <75 microns	None	55.5	52.0	52.5	53.5	54.0	25.0	24.5	24.2	9.54
Air-dried, Angstrom mill, dry but particle size not determined	25 hours @ 105 °C	75.0	/5.0							0
: Air-dried, Angstrom mill, slurry milled with distilled water, dried and hand ground to 100% <840 microns	After milling; air-dried 136 hours; 3 hours; 6 60 °C; 3 hours; 8 80 °C	19.0	18.0				9.0	8.5		10.52

^{*}Map sample 14 was used for these tests. It was determined by XRD to contain a major amount of montmorillonite and minor amounts of quartz, clinoptilolite, and feldspar. The total cation contents (MSC + EC) were, in meq/100 g: 1.7 Na, 33.3 Ca, 15.3 Mg, and 0.9 K. Except for D, the as-tested moisture content of a sample was determined by drying a separate subsample at 105 °C for 4 hours minimum. By definition, if not in reality, the moisture content is 0 percent after drying in this manner. Thus, where the test sample itself was so dried, the as-tested moisture was 0 percent (i.e., in D).

Table 13. Effect of aging time on water loss.*

Age-time (hours)	Water loss (ml)	Preparation method (see Table 12 above)
19.6	33.0	A (distilled water)
20.2	30.5	" "
43.7	32.0	11 11
20.8	9.0	" (soda ash tested)
21.5	9.0	11 11
44.4	8.5	" "
19.5	55.5	C (distilled water)
20.0	52.0	" "
20.9	52.5	" "
67.7	54.0	" "
70.1	53.5	11 11
7012	3313	
22.9	25.0	" (soda ash tested)
23.4	24.5	" "
70.0	24.2	" "

^{*}Map sample 14 was used for these tests.

APPENDIX 9. SAMPLE-NUMBER CORRELATIONS

Table 14. Sample-number correlation chart, listed by map number.

	Sample numbers			Sample numbers			Sample numbers			Sample numbers	
Мар	Laboratory	Field	Мар	Laboratory	Field	Map	Laboratory	Field	Map	Laboratory	Field
1	1	860610-1	46	95	860926-21	91	69	860911-7	136	136	870709-22
2	2	860610-2	47	51	860829-1	92	71	860911-9	137	137	870709-23
3	3	860610-3	48	52	860829-2	93	55	860909-2	138	138	870709-24
4	4	860610-4	49	53	860829-3	94	54	860909-1	139	139	870709-25
5	11B	860702-2	50	83	860914-1	95	154	880715-1	140	140	870709-26
6	11A	860702-1	51	88	860923-24	96	142	870907-2	141	34	860812-1
7	12	860702-3	52	87	860923-23	97	143	870907-2	142	32	860811-1
8	96	861006-1	53	85	860923-21	98	26	860731-4	143	33	860811-2
9	44	860827-3	54	86	860923-22	99	25	860731-3	144	10	860620-2
10	45	860827-4	55	89	860924-21	100	153	880629-2	145	13	860709-1
11	46	860827-5	56	90	860924-22	101	56	860909-3	146	30	860807-1
12	112	861009-23	57	133	870611-23	102	23	860731-1	147	29	860806-1
13	37	860826-1	58	134	870611-25	103	24	860731-2	148	7	860618-4
14	43	860827-2	59	92	860924-24	104	27	860731-5	149	8	860618-5
15	39	860826-3	60	93	860924-25	105	66	860911-4	150	9	860618-6
16	38	860826-2	61	132	870610-25	106	67	860911-5	151	31	860810-1
17	118	861015-22	62	131	870610-24	107	68	860911-6	152	28	860805-1
18	117	861015-21	63	129	870610-21	108	64	860911-2	153	144	
19	111	861009-22	64	130	870610-22	109	63	860911-1	154	152	
20	42	860827-1	65	109	861008-24	110	65	860911-3			
21	40	860826-4	66	94	860925-21	111	141	870907-2			
22	49	860828-3	67	91	860924-23	112	74	860912-3			
23	50	860828-4	68	102	861007-24	113	73	860912-2			
24	119	861015-23	69	100	861007-22	114	72	860912-1			
25	110	861009-21	70	101	861007-23	115	19	860718-1			
26	5	860612-1	71	103	861007-25	116	62	860910-9			
27	6	860612-2	72	104	861007-26	117	61	860910-7			
28	105	861008-1	73	123	870603-21	118	59	860910-5			
29	41	860826-5	74	106	861008-21	119	60	860910-6			
30	47	860828-1	75	107	861008-22	120	75	860912-4			
31	48	860828-2	76	108	861008-23	121	78	860913-1			
32	97	861006-21	77	18	860717-2	122	79	860913-2			
33	122	861017-23	78	147	870814-22	123	58	860910-4			
34	113	861014-21	79	150	870814-25	124	80	860913-3			
35	114	861014-22	80	151	870814-26	125	81	860913-4			
36	115	861014-23	81	99	861007-21	126	82	860913-5			
37	116	861014-24	82	17	860717-1	127	57	860910-1			
38	127	870604-23	83	14	860717-1	128	76	860910-1			
39	128	870604-23	84	15	860716-1	129	76 77	860912-6			
40	120	861017-21	85	16	860716-2	130	20	860718-2			
	121	861017-21	86	145	870814-27	131	20	860718-3			
41	124		87	148							
42	124	870604-20 870604-21			870814-23 870811-21	132	22 35	860718-4			
43			88	146		133	35 36	860812-2			
44 45	126	870604-22	89	149	870814-24	134	36 125	860812-3			
45	98	861007-1	90	70	860911-8	135	135	870709-2			

Table 15. Sample-number correlation chart, listed by laboratory number.

	Sample number:	s		ample umber	s		Sample number			Sample number	
Laboratory	Мар	Field	Laboratory	Мар	Field	Laboratory	Map	Field	Laboratory	Map	Field
1	1	860610-1	45	10	860827-4	91	67	860924-2	136	136	870709-22
2	2	860610-2	46	11	860827-5	92	59	860924-2	137	137	870709-23
3	3	860610-3	47	30	860828-1	93	60	860924-2	138	138	870709-24
4	4	860610-4	48	31	860828-2	94	66	860925-2	139	139	870709-25
5	26	860612-1	49	22	860828-3	95	46	860926-2	140	140	870709-26
6	27	860612-2	50	23	860828-4	96	8	861006-1	141	111	870907-21
7	148	860618-4	51	47	860829-1	97	32	861006-2	142	96	870907-22
8	149	860618-5	52	48	860829-2	98	45	861007-1	143	97	870907-23
9	150	860618-6	53	49	860829-3	99	81	861007-2	144	153	
10	144	860620-2	54	94	860909-1	100	69	861007-2	145	86	870814-27
11A	6	860702-1	55	93	860909-2	101	70	861007-2	146	88	870811-21
11B	5	860702-2	56	101	860909-3	102	68	861007-2	147	78	870814-22
12	7	860702-3	57	127	860910-1	103	71	861007-2	148	87	870814-23
13	145	860709-1	58	123	860910-4	104	72	861007-2	149	89	870814-24
14	83	860716-1	59	118	860910-5	105	28	861008-1	150	79	870814-25
15	84	860716-2	60	119	860910-6	106	74	861008-2	151	80	870814-26
16	85	860716-3	61	117	860910-7	107	75	861008-2	152	154	
17	82	860717-1	62	116	860910-9	108	76	861008-2	153	100	880629-2
18	77	860717-2	63	109	860911-1	109	65	861008-2	154	95	880715-1
19	115	860718-1	64	108	860911-2	110	25	861009-2	201	,,	300.20
20	130	860718-2	65	110	860911-3	111	19	861009-2			
21	131	860718-3	66	105	860911-4	112	12	861009-2			
22	132	860718-4	67	106	860911-5	113	34	861014-2			
23	102	860731-1	68	107	860911-6	114	35	861014-2			
24	102	860731-2	69	91	860911-7	115	36	861014-2			
25	99	860731-2	70	90	860911-8	116	37	861014-2			
				92	860911-8	117	18	861015-2			
26	98	860731-4	71					861015-2			
27	104	860731-5	72	114	860912-1	118	17				
28	152	860805-1	73	113	860912-2	119	24	861015-2			
29	147	860806-1	74	112	860912-3	120	40	861017-2			
30	146	860807-1	75	120	860912-4	121	41	861017-2			
31	151	860810-1	76	128	860912-5	122	33	861017-2			
32	142	860811-1	77	129	860912-6	123	73	870603-2			
33	143	860811-2	78	121	860913-1	124	42	870604-2			
34	141	860812-1	79	122	860913-2	125	43	870604-2			
35	133	860812-2	80	124	860913-3	126	44	870604-2			
36	134	860812-3	81	125	860913-4	127	38	870604-2			
37	13	860826-1	82	126	860913-5	128	39	870604-2			
38	16	860826-2	83	50	860914-1	129	63	870610-2			
39	15	860826-3	85	53	860923-21	130	64	870610-2			
40	21	860826-4	86	54	860923-22	131	62	870610-2			
41	29	860826-5	87	52	860923-23	132	61	870610-2			
42	20	860827-1	88	51	860923-24	133	57	870611-2			
43	14	860827-2	89	55	860924-21	134	58	870611-2			
44	9	860827-3	90	56	860924-22	135	135	870709-2			

STATE OF OREGON DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES DONALD A. HULL, STATE GEOLOGIST

Bentonite in Oregon:
Occurrences, Analyses, and Economic Potential
By Jerry J. Gray, Ron P. Geitgey, and Gary L. Baxter

Table 1. Bentonite (Na- and Ca-Bentonite) and fuller's earth (Ca-bentonite) sold or used by domestic producers, by kind and by use

Plate 1

ear						tons, U.S. Bur									
			1975					1976					1977		
ype of bentonite		Ca-bentonite		Na-bentonite			Ca-bentonit	e	Na-bentonite			Ca-bentonit	te	Na-bentonite	
	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswelling	g Total	(swelling)	Grand tota
se															
omestic:															
Adhesives			0	3	3		W	W	W	W		W	W	4,922	4,92
Animal feed		49,774	49,774	126,284	176,058			0	156,652	156,652		84,704	84,704	110,222	194,92
Building brick			0	1,135	1,135			0		0		W	W	W	-
Catalysts (oil refining)		7,418	7,418	42	7,460		2,208	2,208	9	2,217		12,133	12,133		12,13
Cement, portland	w		W	336	336	W		W	250	250			0	450	45
Drilling mud		25,809	25,809	710,446	736,255	5,478	23,451	28,929	950,099	979,028		22,205	22,205	1,037,962	1,060,16
Fertilizers	12,065	8,406	20,471	710,440	20,471	9,309	9,160	18,469		18,469	10,857	2,380	13,237	30	13,26
Filtering, etc. 1		112,699	112,699	5,687	118,386	2,113	190,972	193,085	3,969	197,054		137,313	137,313	33,037	170,35
Foundry sand binder		242,133	242,133	465,800	707,933	2,113	288,769	288,769	357,704	646,473		289,559	289,559	577,746	867,30
Glazes, glass, enamels			0	141	141			0	337,704 W	040,473		207,337	209,339	120	1
Gypsum products			0	383	383			0	470	470			0	303	30
** *			•					0					0		
Medical, pharmaceutical, cosmetic		58	58	2,019	2,077			-	1,533	1,533			160 262	4,498	4,49
Oil and grease absorbents	148,141		148,141		148,141	120,954	 w	120,954		120,954	168,362		168,362		168,36
Paint			0	4,102	4,102		"	W	W	W			0	16,516	16,51
Paper coating/filling			0		0			0		0			0		
Pelletizing (iron ore)			0	878,022	878,022			0	868,947	868,947			0	629,353	629,35
Pesticides and related products	49,250	2,462	51,712	517	52,229	50,839	3,556	54,395	50	54,445	57,295	1,740	59,035	3,260	62,29
Pet absorbent	222,864		222,864	30,134	252,998	294,722		294,722	35,416	330,138	196,066	5	196,071	25,496	221,56
Tile		8,054	8,054		8,054		46,999	46,999	1,925	48,924		91	91		9
Waterproofing and sealing		1,820	1,820	33,629	35,449		2,402	2,402	63,389	65,791		18,589	18,589	59,752	78,34
Miscellaneous ²	19,051	3,052	22,103	61,984	84,087	44,978	187	45,165	13,766	58,931	62,468	5,510	67,978	103,795	171,77
Total	451,371	461,685	913,056	2,320,664	3,233,720	528,393	567,704	1,096,097	2,454,179	3,550,276	495,048	574,229	1,069,277	2,607,462	3,676,73
exports:															
Drilling mud			0	128,848	128,848			0	184,572	184,572			0		
Fertilizers	W		W		W			0		0		200	200	150,771	150,97
Foundry sand binder		12,821	12,821	154,391	167,212		16,331	16,331	153,749	170,080		16,538	16,538	168,683	185,22
Oil and grease absorbents	4,544		4,544		4,544	141		141		141	39,669		39,669		39,66
Pelletizing (iron ore)			0	142,839	142,839			0	129,596	129,596			0	203,501	203,50
Pesticides and related products			0		0			0		0		·	0		,
Pet absorbent	5,734		5,734		5,734	22,830		22,830		22,830	33,739		33,739		33,73
Miscellaneous	7,981		7,981	8,019	16,000	7,997	13,068	21,065	1,182	22,247	1,418	184	1,602	24,919	26,52
	18,259	12,821	31,080	434,097	465,177	30,968	29,399	60,367	469,099	529,466	74,826	16,922	91,748	547,874	639,62
Total	469,630	474,506	944,136	2,754,761	3,698,897	559,361		1,156,464	2,923,278	4,079,742	569,874	591,151		3,155,336	4,316,36

Year			1978					1979					1980		
Type of bentonite		Ca-bentonit	e	Na-bentonite			Ca-bentoni	te	Na-bentonite			Ca-bentonite	е	Na-bentonite	
	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswelling	g Total	(swelling)	Grand total	Fuller's earth	Nonswelling	Total	(swelling)	Grand tota
Use															
Domestic:															
Adhesives		W	W	2,747	2,747		W	W	1,219	1,219		W	w	W	
Animal feed		63,109	63,109	148,161	211,270		70,234	70,234	113,813	184,047	20	64,057	64,077	106,379	170,4
Building brick		W	W		W		W	W		W		W	W		
Catalysts (oil refining)		16,843	16,843		16,843		4,511	4,511		4,511		8,722	8,722		8,7
Cement, portland			0	W	W			0	W	W			0	W	,
Drilling mud	26,189	412	26,601	1,143,635	1,170,236	23,578	14,658	38,236	1,261,477	1,299,713	1,453	59,061	60,514	1,374,150	1,434,6
Fertilizers	15,774	2,420	18,194	17	18,211	19,796	4,764	24,560		24,560	24,532		24,532	4,658	29,1
Filtering, etc. 1		146,933	146,933	9,379	156,312		109,552	109,552	6,784	116,336		109,172	109,172	2,787	111,9
Foundry sand binder		337,889	337,889	697,939	1,035,828		300,576	300,576	595,697	896,273		228,550	228,550	403,530	632,0
Glazes, glass, enamels		W	W	W	W			0	W	W			0	W	,
Gypsum products			0	W	W			0	W	W			0		
Medical, pharmaceutical, cosmetic		50	50	1,232	1,282			0	3,295	3,295			0	2,451	2,4
Oil and grease absorbents	191,596		191,596		191,596	165,174		165,174		165,174	158,796		158,796		158,7
Paint		213	213	26,767	26,980			0	13,905	13,905	·		0	14,111	14,1
Paper coating/filling	3,245		3,245	´	3,245	1,773		1,773	·	1,773			0		•
Pelletizing (iron ore)		183	183	939,274	939,457	·	13,504	13,504	888,204	901,708		849	849	861,538	862,3
Pesticides and related products	56,294	1,496	57,790	3,259	61,049	67,847	1,403	69,250	2,787	72,037	72,351	3,251	75,602	2,694	78,2
Pet absorbent	260,249	´	260,249	W	260,249	250,177		250,177	W	250,177	253,875	W	253,875		253,8
Tile			,		•			0		0			0		
Waterproofing and sealing		2,952	2,952	71,447	74,399		34,372	34,372	41,321	75,693		2,160	2,160	89,494	91,6
Miscellaneous ²	37,365	42,040	79,405	202,364	281,769	49,398	423	49,821	233,481	283,302	54,994	86,043	141,037	126,941	267,9
Total	590,712	614,540	1,205,252	3,246,221	4,451,473	577,743	553,997	1,131,740	3,161,983	4,293,723	566,021	561,865	1,127,886	2,988,733	4,116,6
Exports:															
Drilling mud			0	171,388	171,388			0	180,067	180,067		1,782	1,782	331,302	333,0
Fertilizers			0		0	"		0		0			0		
Foundry sand binder		16,998	16,998	222,202	239,200		16,964	16,964	250,066	267,030		12,646	12,646	222,681	235,3
Oil and grease absorbents	11,940		11,940		11,940	20,457		20,457		20,457	24,732		24,732		24,7
Pelletizing (iron ore)			0	164,086	164,086			0	172,515	172,515			0		
Pesticides and related products			0		0			0		0			0		
Pet absorbent	5,665		5,665		5,665	9,100		9,100		9,100	10,741		10,741		10,7
Miscellaneous	1,459	1,662	3,121	30,508	33,629	1,650	4,531	6,181	81,952	88,133	6,315	5,320	11,635	60,290	71,9
Total	19,064	18,660	37,724	588,184	625,908	31,207	21,495	52,702	684,600	737,302	41,788	19,748	61,536	614,273	675,8
Grand total	609,776	633,200	1,242,976	3,834,405	5,077,381	608,950	575,492	1,184,442	3,846,583	5,031,025	607,809	581,613	1,189,422	3,603,006	4,792,4

Year			1981					1982					1983		
Type of bentonite		Ca-bentonite	9	Na-bentonite			Ca-bentoni	te	Na-bentonite			Ca-bentonit	9	Na-bentonite	
	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswellin	g Total	(swelling)	Grand total	Fuller's earth	Nonswelling	Total	(swelling)	Grand total
Use															
Domestic:															
Adhesives		W	0	W	W			0	179	179			0	6,688	6,688
Animal feed		57,855	57,855	99,258	157,113		66,334	66,334	74,148	140,482		38,737	38,737	98,220	136,957
Building brick			0	W	W			0		0			0		0 .
Catalysts (oil refining)		7,749	7,749	5	7,754		4,311	4,311	4	4,315		10,329	10,329	178	10,507
Cement, portland			0	W	W			0	W	W			0	W	W
Drilling mud	2,027	60,554	62,581	2,004,088	2,066,669		15,275	15,275	1,409,072	1,424,347		580	580	1,155,189	1,155,769
Fertilizers	22,841		22,841	4,054	26,895	19,285		19,285	2,749	22,034	13,331		13,331		13,331
Filtering, etc. 1		158,364	158,364	2,610	160,974		147,255	147,255	1,936	149,191	1,576	103,031	104,607	8,463	113,070
Foundry sand binder		270,289	270,289	521,430	791,719		186,243	186,243	328,028	514,271		207,224	207,224	372,726	579,950
Glazes, glass, enamels			0	W	W			0	W	W			0	W	W
Gypsum products			0		0			0		0			0		0
Medical, pharmaceutical, cosmetic			0	2,818	2,818			0	8,050	8,050	2		2	4,437	4,439
Oil and grease absorbents	246,821		246,821		246,821	232,833		232,833		232,833	193,946		193,946		193,946
Paint			0	14,412	14,412			0	12,998	12,998			0	9,223	9,223
Paper coating/filling			0		0			0		0			0		0
Pelletizing (iron ore)			0	884,976	884,976			0	396,506	396,506			0	301,357	301,357
Pesticides and related products	66,669	506	67,175	2,872	70,047	75,210	366	75,576	4,731	80,307	83,858	506	84,364	7,282	91,646
Pet absorbent	304,080	W	304,080		304,080	359,958	W	359,958		359,958	485,844	W	485,844		485,844
Tile			0		0			0		0			0		0
Waterproofing and sealing		1,897	1,897	88,882	90,779		17,939	17,939	87,527	105,466		20,079	20,079	73,534	93,613
Miscellaneous	36,378	63,944	100,322	71,168	171,490	81,557	60,155	141,712	65,817	207,529	51,005	120,488	171,493	74,116	245,609
Total	678,816	621,158	1,299,974	3,696,573	4,996,547	768,843	497,878	1,266,721	2,391,745	3,658,466	829,562	500,974	1,330,536	2,111,413	3,441,949
Exports:															
Drilling mud			0	364,342	364,342			0	227,409	227,409			0	178,037	178,037
Fertilizers			0		0			0		0			0		0
Foundry sand binder		13,956	13,956	203,928	217,884		109	109	53,441	53,550		126	126	34,943	35,069
Oil and grease absorbents	33,112		33,112		33,112	29,783		29,783		29,783	36,469		36,469		36,469
Pelletizing (iron ore)			0	37,771	37,771			0		0			0		0
Pesticides and related products			0		0			o		0	458		458		458
Pet absorbent	27,283	~	27,283		27,283	27,513		27,513		27,513	12,898		12,898		12,898
Miscellaneous ²	334	2,319	2,653	7,111	9,764	343	2,248	2,591	71,970	74,561	3,011	2,310	5,321	59,067	64,388
Total	60,729	16,275	77,004	613,152	690,156	57,639	2,357	59,996	352,820	412,816	52,836	2,436	55,272	272,047	327,319
Grand total	739,545	637,433	1,376,978	4,309,725	5,686,703	826,482	500,235	1,326,717	2,744,565	4,071,282	882,398	503,410	1,385,808	2,383,460	3,769,268


Year			1984					1985					1986		
Type of bentonite		Ca-bentonite	9	Na-bentonite			Ca-bentonit	e	Na-bentonite			Ca-bentonit	e	Na-bentonite	
	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswelling	Total	(swelling)	Grand total	Fuller's earth	Nonswelling	Total	(swelling)	Grand total
Use															
Domestic:															
Adhesives			0	6,757	6,757		2,000	2,000	6,938	8,938			0	11,302	11,302
Animal feed		49,811	49,811	136,321	186,132		38,265	38,265	92,219	130,484		43,262	43,262	69,164	112,426
Building brick			0		0			0		0			0		0
Catalysts (oil refining)		8,763	8,763		8,763		5,748	5,748	2,470	8,218		5,232	5,232	147	5,379
Cement, portland			0	W	W			0	W	W			0	W	W
Drilling mud		14,878	14,878	1,346,191	1,361,069		17,913	17,913	1,168,728	1,186,641		5,193	5,193	1 ,031,555	1,036,748
Fertilizers	10,576		10,576		10,576	10,482		10,482		10,482	7,379		7,379		7,379
Filtering, etc. 1	784	1,074	1,858	5,119	6,977		36,500	36,500	3,071	39,571		165,679	165,679	2,110	167,789
Foundry sand binder		227,886	227,886	520,177	748,063		206,388	206,388	522,199	728,587		215,004	215,004	401,784	616,788
Glazes, glass, enamels			0	W	W			0	W	W			0		0
Gypsum products			0		0			0		0			0		0
Medical, pharmaceutical, cosmetic			0	5,081	5,081			0	3,968	3,968			0	7,321	7,321
Oil and grease absorbents	220,878	100,951	321,829	45	321,874	309,015	34,448	343,463	45	343,508	200,694	8,557	209,251		209,251
Paint			0	10,852	10,852			0	7,161	7,161			0	8,446	8,446
Paper coating/filling			0		0			0		0			0		0
Pelletizing (iron ore)			0	404,493	404,493			0	290,567	290,567			0	262,419	262,419
Pesticides and related products	120,223	425	120,648	10,268	130,916	164, 546	897	165,443	235	165,678	92,675	1,163	93,838	4,214	98,052
Pet absorbent	506,279		506,279		506,279	566,869		566,869		566,869	610,457		610,457		610,457
Tile			0		0			0		0			0		0
Waterproofing and sealing		1,597	1,597	72,795	74,392		3,432	3,432	119,876	123,308		4,424	4,424	935	5,359
Miscellaneous ²	50,752	103,016	153,768	67,524	221,292	50,494	126,302	176,796	79,334	256,130	61,462	77,042	138,504	110,465	248,969
Total	909,492	508,401	1,417,893	2,585,623	4,003,516	1,101,406	471,893	1,573,299	2,296,811	3,870,110	972,667	525,556	1,498,223	1 ,909,862	3,408,085
Exports:															
Drilling mud			0	153,188	153,188			0	117,130	117,130			0	183,934	183,934
Fertilizers			0		0			0		0			0		0
Foundry sand binder		1,310	1,310	161,038	162,348		24,978	24,978	142,420	167,398		52,760	52,760	104,972	157,732
Oil and grease absorbents	38,138		38,138		38,138	18,701		18,701		18,701	3,031		3,031		3,031
Pelletizing (iron ore)			0		0			0		0			0		0
Pesticides and related products	373		373		373	971		971		971	2,589		2,589		2,589
Pet absorbent	12,295		12,295		12,295	11,434		11,434		11,434	9,571		9,571		9,571
Miscellaneous	486	1,638	2,124	26,742	28,866	6,137	1,078	7,215	140,970	148,185	1,348	9,245	10,593	26,714	37,307
Total	51,292	2,948	54,240	340,968	395,208	37,243	26,056	63,299	400,520	463,819	16,539	62,005	78,544	315,620	394,164
Grand total	960,784	511,349	1,472,133	2,926,591	4,398,724	1,138,649	497,949	1,636,598	2,697,331	4,333,929	989,206	587,561	1,576,767	2,225,482	3,802,249

W = Withheld to avoid disclosing company proprietary data; included with "Miscellaneous"

1Clarifying and decolorizing mineral, animal, and vegetable greases and desiccants

Clarifying and decolorizing mineral, animal, and vegetable greases and desiccants

May include bentonite used for animal feed, chemical manufacturing; paint; fiberglass; firebricks, blocks, and shapes; gypsum products; mineral wool and insulation; paper coating and filling; pet waste absorbents; plastics; rubber; ink; waterproofing and sealing, uses not specified; and data indicated by symbol "W".



Bentonite in Oregon: Occurrences, Analyses, and Economic Potential By Jerry J. Gray, Ron P. Geitgey, and Gary L. Baxter

Plate 3

Table 4. Survey data, Oregon bentonite study.

	Loca	tion description	Sample	-site description	P h y	sical tests			X-ray diffraction m				Chemical Tests	
					Swell (% expansion over 24 hr) *		Water loss (not API test; see text)	c	lay	Non-clay		Water-soluble cations (milliequivalents/100 grams)	Exchangeable cations (milliequivalents/100 grams)	Water-soluble cation + exchangeable cations (milliequivalents/100 grams)
Map sample				Sample interval (ft) H=horizontal	Moisture (%) after air As Trea	ted	As Treated							Map sample
1 Gill		Area Subsect	20 3N 21E Road cut	Type V=vertical Shallow pit -	8.00 0	40 75.29 -	TE 131.0	ontmorillonite m	Kaolinite Illite Quartz Cri	tr -	te Feldspar Calcite Gypsum Other	Na Ca Mg K Li Total 0.53 0.24 0.10 0.19 <0.01 1.07	Na Ca Mg K Total 0.29 21.00 10.60 0.54 32.43	Na Ca Mg K Total no. 0.82 21.24 10.70 0.73 33.49 1
2 Unio 3 Unio 4 Unio 5 Wash	on Rondowa 7.5	Troy Basin W,Sk Troy Basin W,Sk Troy Basin W,Sk Paisley Canyon SE,S	W 18 3N 40E Road cut W 18 3N 40E Road cut	Grab - Grab - Grab - Grab -	6.91 0 - 0 6.17 0 6.86 30	0 64.85 - - 83.35 - 60 74.79 - 40 37.35 -	TE	m - m	tr tr	tr - tr -	Noncrystalling	0.28 0.11 0.06 0.16 0.01 0.62 Sample depleted	0.21 14.00 11.10 0.51 25.82 Sample depleted	0.49 14.11 11.16 0.67 26.43 2 Sample depleted 3 0.43 9.95 6.33 0.56 17.27 4 0.62 9.68 7.46 0.89 18.65 5
6 Wash	nington Buxton 7.5	Paisley Canyon NE,N Paisley Canyon SE,N	NW 7 2N 4W Road cut	Grab 0-200 H	6.56 - 2.76 0	 20 40.22 -	TE 140.0	m tr	tr	tr -		0.30 0.07 0.04 0.13 0.01 0.55 0.48 0.20 0.12 0.27 <0.01 1.07	0.37 15.70 8.37 0.66 25.10 0.28 3.21 2.54 0.55 6.58	0.67 15.77 8.41 0.79 25.64 6 0.76 3.41 2.66 0.82 7.65 7
	tilla Canyon Mtn. 7.5 co Antelope 15	Ukiah SW,N Clarno NW,S Clarno NW,N	NE 15 5S 31E Road cut SW 35 7S 18E Road cut	Grab - Shallow pit - Shallow pit -	7.12 0 7.36 40 6.73 50	60 >10.00 - 0 >10.00 - 700 15.28 9.36	90.0 24.0 26.0 12.0 33.0 14.0	m m	tr - tr tr tr	tr - tr - tr -	 - tr tr	0.57 0.51 0.30 0.09 <0.01 1.48 11.40 4.90 3.65 0.54 0.01 20.50 5.31 2.33 1.92 0.54 0.02 10.12	0.06 10.90 5.58 0.10 16.64 2.41 18.30 12.40 0.45 33.56 1.52 20.30 9.61 0.45 31.88	0.63 11.41 5.88 0.19 18.11 8 13.81 23.20 16.05 0.99 54.05 9 6.83 22.63 11.53 0.99 41.98 10
11 Wasc 12 Gran	nt Dale 15	Clarno NW,N Desolation Creek SW,S	SE 27 7S 32E Road cut	Shallow pit - Channel 0-10 V	7.63 20 13.44 100	540 >10.00 - 140 >10.00 10.30	57.5 15.5 20.0 10.0	m M	tr	 tr -	- tr	4.06 2.82 1.30 0.58 0.01 8.77 0.54 0.48 0.25 0.17 <0.01 1.45	0.75 24.90 10.10 0.34 36.09 0.20 21.80 13.30 0.24 35.54	4.81 27.72 11.40 0.92 44.85 11 0.74 22.28 13.55 0.41 36.98 12
13 Wasc 14 Wasc 15 Wasc	co Antelope 15	Willowdale/Antelope SW,N Antelope SE,N Rancho Rajneesh SW,S	NW 4 8S 18E Road cut	Shallow pits - Channel 0-3 V Channel 0-30 V	9.35 0 10.81 80 7.12 380	820 >10.00 - 60 >10.00 - 820 >10.00 7.68	22.5 7.5 32.0 9.0 12.0 9.0	m M m	tr tr M	tr - tr -	tr tr tr	5.42 1.80 0.86 0.55 0.01 8.64 1.02 1.09 0.42 0.33 <0.01 2.87 18.70 13.70 6.15 0.45 0.01 39.01	1.81 39.40 12.80 0.64 54.65 0.66 32.20 14.90 0.60 48.36 10.10 16.30 3.59 0.89 30.88	7.23 41.20 13.66 1.19 63.28 13 1.68 33.29 15.32 0.93 51.22 14 28.80 30.00 9.74 1.34 69.88 15
16 Wasc 17 Gran 18 Gran	nt Monument 15	Rancho Rajneesh SW,S Monument SW,N Sunken Mt. Landside NW.S	NE 5 9S 27E Road cut	Shallow pit - Channel 0-6 V Channel 0-4 V	7.65 420 8.94 40 7.53 0	820 9.22 5.44 60 >10.00 - 0 >10.00 -	13.0 9.5 31.0 21.5 31.0 20.5	n n	M tr - tr	tr	- tr	23.90 11.40 3.70 0.28 0.01 39.29 9.60 4.50 1.46 0.41 <0.01 15.98 3.89 5.50 1.05 0.14 <0.01 10.59	6.92 23.30 5.67 0.43 36.32 8.52 14.20 1.61 0.22 24.55 6.07 15.00 1.78 0.15 23.00	30.82 34.70 9.37 0.71 75.60 16 18.12 18.70 3.07 0.63 40.52 17 9.96 20.50 2.83 0.29 33.58 18
19 Gran		Olive Lake NE,S Richardson Ranch NW	SW 13 9S 34E Road cut	Channel 0-2 V Shallow pit -	11.67 100 9.89 100	150 >10.00 - 40 >10.00 9.75	31.0 6.5 13.0 10.0	M M		tr - tr -	 tr tr	0.24 0.50 0.22 0.10 <0.01 1.07 8.80 10.10 1.48 0.73 0.01 21.12	0.06 26.10 12.10 0.15 38.41 8.59 31.10 2.53 1.22 43.44	0.30 26.60 12.32 0.25 39.47 19 17.39 41.20 4.01 1.95 64.55 20
21 Jeff 22 Whee 23 Whee		Cherry Creek Ranch SW,N Mitchell SE,S Mitchell SE,N	SE 22 10S 22E Road cut	Grab - Shallow pit - Shallow pit -	9.74 280 10.39 160 4.54 260	80 >10.00 6.97 820 6.28 5.16 220 9.12 8.08	17.0 10.0 18.0 8.5 12.5 7.5	M m M	m tr 	tr - - tr - tr	- tr	19.90 10.30 5.39 0.39 0.01 35.99 8.20 6.40 2.31 0.30 <0.01 17.22 10.40 11.30 2.74 0.47 <0.01 24.92	11.80 30.10 10.20 0.75 52.85 2.75 33.60 8.07 0.21 44.63 3.00 32.80 5.14 0.22 41.16	31.70
24 Gran 25 Bake		China Peak SW,S Whitney SW,S		Shallow pits 0-60 V Channel 0-3 H	8.18 40 6.18 20	40 >10.00 - 80 >10.00 -	28.0 15.5 23.5 20.0	m tr	tr m - tr	tr - tr -	: : : :	9.50 1.44 0.38 0.11 <0.01 11.44 0.25 0.48 0.26 0.07 <0.01 1.07	13.90 24.80 3.58 0.22 42.50 0.32 10.10 6.21 0.41 17.04	23.40 26.24 3.96 0.33 53.93 24 0.57 10.58 6.47 0.48 18.10 25
26 Bake 27 Bake 28 Bake	Bowen Valley 7.5 er Encina 7.5	Gyllenburg Ranch NE Gyllenburg Ranch NE Sutton Creek SW,S	SW 8 10S 41E Road cut	Shallow pit - Grab - Channel 0-3 V	8.86 40 3.04 0 5.66 20	40 16.03 - 20 69.08 - 160 >10.00 -	88.0 20.0 TE 92.0 59.0 29.0 16.5 13.0	m m	tr m M	m - 		2.93 0.36 0.18 0.28 0.01 3.76 2.06 9.50 6.22 1.59 0.01 19.38 1.74 0.66 0.66 0.08 <0.01 3.15 10.10 8.10 0.83 0.87 0.01 19.91	2.65 21.70 13.20 0.82 38.37 0.12 7.76 5.55 0.26 13.69 3.17 13.00 9.16 0.55 25.88 8.64 27.50 1.05 1.35 38.54	5.58 22.06 13.38 1.10 42.12 26 2.18 17.26 11.77 1.85 33.06 27 4.91 13.66 9.82 0.63 29.02 28
29 Jeff 30 Whee		Willow Creek SW,S Mitchell SE,S Mitchell NW,S	SE 19 11S 21E Road cut	Channel 0-30 V Shallow pit - Shallow pit -	8.18 110 5.29 0 8.44 190	40 >10.00 11.10 160 >10.00 -	16.5 13.0 40.0 20.0	m m	tr - tr	tr -	- tr m dolomite	10.10 8.10 0.83 0.87 0.01 19.91 29.70 2.71 3.78 0.43 <0.01 36.63 19.00 9.20 4.76 0.70 0.02 33.68	8.64 27.50 1.05 1.35 38.54 0.80 14.60 17.00 0.27 32.67 19.60 22.10 5.79 0.88 48.37	18.74 35.60 1.88 2.22 58.44 29 30.50 17.31 20.78 0.70 69.29 30 38.60 31.30 10.55 1.58 82.03 31
32 Gran 33 Whee 34 Gran	nt Picture Rock 15 eler Antone 7.5	John Day Beds NE,S Antone NE,S Rattle Snake Creek NE,S	SW 6 11S 26E Outcrop SW 27 12S 24E Road cut	Shallow pit - Channel 0-6 V Channel 0-3 V	5.53 90 6.35 80 9.11 40	350 25.91 15.39 40 >10.00 - 160 >10.00 -	20.5 17.5 32.0 17.5 82.0 29.0	- m	tr tr	- m - m	m	18.60 6.00 2.04 0.37 0.02 27.03 11.00 6.50 1.30 0.27 0.01 19.08 14.10 1.79 1.27 0.58 <0.01 17.75	8.74 14.80 1.15 0.12 24.81 7.44 10.40 0.88 0.02 18.74 1.99 14.70 9.02 0.18 25.89	27.34 20.80 3.19 0.49 51.82 32 18.44 16.90 2.18 0.29 37.81 33 16.09 16.49 10.29 0.76 43.63 34
35 Gran	nt Picture Gorge 15	Rattle Snake Creek NE, S	SW 29 12S 26E Outcrop	Channel 15-30 V Channel 0-15 V	7.95 0 8.57 0	80 >10.00 - 160 >10.00 -	TE 34.0 88.0 29.5	m	tr 	tr - tr -		9.00 9.20 5.28 0.98 <0.01 24.47 9.10 0.79 0.46 0.48 <0.01 10.84	0.42 13.60 6.74 0.19 20.95 1.73 15.80 8.21 0.29 26.03	9.42 22.80 12.02 1.17 45.41 35 10.83 16.59 8.67 0.77 36.86 36
37 Gran 38 Gran 39 Gran	nt Picture Gorge 15 nt Picture Gorge 15	Rattle Snake Creek NE, N	SW 29 12S 26E Outcrop NW 29 12S 26E Outcrop NW 29 12S 26E Outcrop NW 36 12S 27E Outcrop	Shallow pit - Channel 0-12 V Channel 12-17 V	8.43 60 9.04 40	110 1.76 - 240 >10.00 - 240 >10.00 - 140 >10.00 -	73.5 28.5 47.0 15.0 88.0 22.0 49.0 28.0	12. En				13.10 10.70 6.10 1.03 <0.01 30.94 21.80 4.40 3.09 1.10 0.01 30.40 12.70 1.93 0.96 1.54 <0.01 17.14 11.90 0.81 0.66 0.26 <0.01 13.64	0.55 16.10 8.21 0.16 25.02 2.89 15.90 10.80 0.28 29.87 3.25 32.00 15.20 0.81 51.26	24.69 20.30 13.89 1.38 60.26 38 15.95 33.93 16.16 2.35 68.39 39
40 Gran 41 Gran 42 Gran	nt Dayville 7.5	Dayville SE,N Dayville SE,N Dayville SE,N	NW 36 12S 27E Outcrop	Channel 0-6 V Channel 0-20 V Drill cuttings 1-5 V	8.63 20	160 >10.00 - 160 >10.00 -	53.0 23.5 49.0 22.0	m m	tr	tr -		2.50 2.93 1.83 0.47 <0.01 7.74 3.30 0.64 0.45 0.14 <0.01 4.54		2.65 21.53 12.03 0.63 36.84 41
43 Gran 44 Gran 45 Bake	nt Dayville 7.5 nt Dayville 7.5	50' below sample 42 SE,N 50' below sample 42 SE,N Hereford NE,S	NW 36 12S 27E Outcrop NW 36 12S 27E Outcrop	Drill cuttings 1.5-4 V Drill cuttings 4-6.5 V Shallow pit -	8.01 40 7.91 40	260 >10.00 - 340 1.31 - 180 >10.00 -	36.0 15.5 41.0 16.0 27.0 18.0	m m tr	tr 		tr	3.86 1.53 1.25 0.40 <0.01 7.05 3.09 0.76 0.49 0.36 <0.01 4.71		4.26 15.13 10.38 0.50 30.27 43 3.73 16.56 10.14 0.55 30.98 44
46 Croo		O'Neil Sand & Gravel SE,N Ochoco Reservoir SE,N	NE 30 14S 14E Outcrop NE 31 14S 18E Road cut	Shallow pit - Shallow pit -	7.24 0 6.38 40	20 >10.00 - 140 >10.00 -	TE TE 47.0 13.0	m m		tr -	 tr	0.48 0.32 0.30 0.17 <0.01 1.28 1.92 3.70 0.67 0.30 <0.01 6.59	0.53 23.00 1.84 0.29 25.66	2.45 26.70 2.51 0.59 32.25 47
48 Croc 49 Croc 50 Malh	ok Lookout Mtn. 15	Summit Prairie SE,	NE 31 14S 18E Road cut NE 31 14S 21E Rock quarry SW 20 15S 44E Stream cut	Grab - Grab - Channel 0-7 V	13.77 140	0 >10.00 - 100 10.97 - >840 4.96 2.61	135.0 16.5 23.0 8.5 12.0 5.5	m M M		m - 	tr	0.60 3.07 0.68 0.35 <0.01 4.71 0.22 1.80 0.63 0.26 <0.01 2.92 9.80 7.50 2.83 0.50 0.01 20.64	0.07 28.30 4.69 0.22 33.28 0.41 41.30 12.60 0.43 54.74 1.33 27.80 10.00 0.30 39.43	0.63 43.10 13.23 0.69 57.65 49
51 Croo 52 Croo 53 Croo	ok Eagle Rock 15	Crooked River Reservoir SE,S Crooked River Reservoir SW,N Crooked River Reservoir NE,N	NE 33 16S 17E Road cut	Channel 0-15 H Shallow pit - Shallow pit -	6.08 60	0 >10.00 - 20 >10.00 13.31 0 >10.00 -	27.5 12.0 17.5 11.5 26.0 12.5	m tr	m		- tr - tr dolomite 		4.39 28.30 21.10 0.47 54.26 13.50 22.60 0.57 0.44 37.11 0.53 11.20 5.69 0.23 17.65	
54 Croo	ok Eagle Rock 15		NE 22 16S 17E Outcrop	Shallow pit - Channel 0-8 V	2.18 0	0 >10.00 - 60 >10.00 11.02	95.0 33.0	tr tr	m - tr	-	tr fluorite		<0.01 9.60 1.75 0.18 11.54	0.36 10.18 1.88 0.27 12.69 54
56 Croc 57 Croc 58 Croc	ok Post 15 ok Committee Creek 7.5		NW 19 16S 20E Outcrop NE 27 16S 20E Outcrop	Channel 0-12 V Channel 0-10 V Channel 0-3 V	6.63 140 8.17 240	100 >10.00 - >840 8.96 4.35 560 7.12 3.29		m tr	tr m	tr -	 - tr		5.82 17.40 10.40 0.73 34.35 29.40 28.00 15.60 0.83 73.83	20.32 21.90 13.37 1.91 57.50 57 55.30 31.04 17.31 1.34 104.99 58
59 Cros	ok Post 15	Crooked River SE,S	SE 35 16S 20E Outcrop SE 35 16S 20E Outcrop	Channel 0-75 V Channel 0-10 V	8.84 200		20.5 14.0 10.0 7.5	m M			tr	17.20 16.10 2.31 0.83 0.01 36.45		
61 Cross 62 Cross 63 Cross 64 Cross	ok Committee Creek 7.5 ok Committee Creek 7.5	Teater Road NE,	SE 35 16S 20E Outcrop NE 30 16S 21E Cat cut NW 29 16S 21E Cat cut NW 29 16S 21E Cat cut	Channel 0-6 V Channel 0-5 V Channel 0-1.5 V Channel 0-1.5 V		220 7.59 3.18 >840 >10.00 - 80 >10.00 - 40 >10.00 -	10.0 6.5 24.5 8.5 43.0 9.5 45.0 7.0	m M M		tr -	tr	10.40 2.28 0.70 1.11 <0.01 14.50 0.48 0.22 0.11 0.17 <0.01 0.99	5.88 29.60 8.15 0.27 43.90	16.28 31.88 8.85 1.38 58.39 62 0.96 52.72 23.21 0.53 77.42 63
65 Gran	nt Seneca 15		NE 31 16S 32E Road cut	Channel 0-4 V Shallow pit -	5.14 0	60 >10.00 -	33.0 18.0 21.0 12.5	 - m		tr -	I	1.04 0.82 0.38 0.08 <0.01 2.33 9.20 5.70 3.50 0.45 0.01 18.86		1.14 10.15 4.20 0.18 15.67 65
67 Cros 68 Gran 69 Gran	nt Izee 15 nt Izee 15	Crooked River SE, Izee SW,I Izee SW,I	NE 31 17S 29E Outcrop NE 31 17S 29E Outcrop	Shallow pit 0-3 V Channel 11-17 V Channel 0-6 V	8.24 100 1.67 0 3.66 20	80 >10.00 - 40 >10.00 - 40 >10.00 -	21.5 9.5 62.0 41.0 110.0 74.0	м - -	m - tr m - tr			0.18 0.23 0.07 0.33 <0.01 0.82		0.21 2.59 1.10 0.50 4.40 68 0.28 4.29 0.97 0.86 6.40 69
70 Gran 71 Gran 72 Gran	nt Izee 15	Izee SW,I Izee SW,I Izee SW,I	NE 31 17S 29E Outcrop	Channel 6-11 V Channel 17-27 V Channel 27-39 V	2.46 0 1.49 0 1.49 0	20 >10.00 - 40 >10.00 - 0 2.90 -	65.0 40.0 75.0 45.0	tr - tr	m tr M				<0.01 3.67 1.13 0.19 5.00 <0.01 3.72 1.22 0.31 5.26 <0.01 4.97 1.63 0.36 6.97	0.22 4.12 1.39 0.67 6.40 71
72 Gran 73 Gran 74 Gran 75 Gran	nt Izee 15 nt Seneca 15	Izee SE,N Silvies River NE,S	NW 31 17S 29E Outcrop	Channel 0-10 V Shallow pit 0-40 H Shallow pit 40-85 H	6.06 60 1.80 0	100 1.35 - 40 >10.00 - 0 >10.00 -	57.0 19.0 118.0 76.0 154.0 94.0	m - -	tr m tr tr			4.44 0.77 0.55 0.38 <0.01 6.15 0.54 1.24 0.36 0.16 <0.01 2.31	0.84 7.80 5.94 0.22 14.80	5.28 8.57 6.49 0.60 20.94 73 0.54 7.32 1.80 0.26 9.92 74
76 Gran 77 Gran	nt Seneca nt Seneca 15	Silvies River NE,S	SW 25 17S 31E Road cut	Shallow pit 85-150 H Shallow pit -	1.47 0 10.78 0	100 >10.00 - 40 >10.00 -	134.0 84.0 147.0 77.0	- tr	m - M - M tr		: : : :	0.79 0.26 0.13 0.06 <0.01 1.25		1.65 11.66 5.94 0.64 19.89 77
78 Croc 79 Croc 80 Croc	ok Gerry Mtn. 7.5	Evergreen Bentonite SW,S	SW 33 18S 21E Bentonite mine SE 35 18S 21E Zeolite mine SW 35 18S 21E Zeolite mine sto	Channel 0-3 V Shallow pit - ockpile Grab -	6.69 30	560 11.73 7.35 80 11.27 - 20 21.86 -	10.0 8.0 54.0 27.0 34.0 23.5	tr		m	tr tr tr	38.60 2.98 2.40 0.23 <0.01 44.22 2.14 0.79 0.29 0.16 <0.01 3.39 10.10 1.88 0.58 0.31 <0.01 12.88		12.14 28.09 3.73 0.65 44.61 79
81 Gran 82 Gran 83 Harr	nt Seneca 15	Izee NE, Sylvies NE, Silvies-Van Road NE, NE, Silvies-Van Road	SE 7 18S 32E Outcrop	Channel 0-10 H Shallow pit - Channel 0-3 V	3.91 0 6.91 0 5.14 10	120 >10.00 - 0 >10.00 - 80 >10.00 -				tr -	tr	0.89 0.27 0.11 0.01 <0.01 1.29		
84 Harr 85 Harr	ney Flag Prairie 15	Silvies-Van Road SW,	NW 14 18S 33E Road Cut NW 14 18S 33E Road Cut	Grab - Grab -	12.04 30 7.25 40	90 >10.00 - 40 >10.00 -	155.0 30.0 93.0 22.5	m -		tr - tr -	: : : :	0.60 0.24 0.11 0.08 <0.01 1.04	0.90 22.20 7.08 1.12 31.30 0.22 13.20 4.58 0.17 18.17	0.82 13.44 4.69 0.25 19.20 85
86 Croc 87 Croc 88 Croc	ok Gerry Mtn. 7.5 ok Gerry Mtn. 7.5	Central Oregon Bentonite SE, S Central Oregon Bentonite SE, S Central Oregon Bentonite NW, S	SE 5 19S 21E Bentonite mill SW 4 19S 21E Bentonite mine	Mill run - Mill run - Channel 0-4 V	5.00 460 5.96 340 8.53 140	320 8.93 6.42 280 11.88 8.51 40 8.72 7.69	9.5 9.0 14.5 9.0	m m	tr	m	tr - tr - m - tr - tr tr	56.80 8.70 2.19 0.40 0.01 68.10 13.30 1.94 0.21 0.34 0.01 15.80	44.20 6.80 0.49 0.33 51.82	19.48 25.24 0.28 0.71 45.71 88
90 Mall	heur Double Mtn. 7.5	Evergreen Bentonite SW,1 Bentonite Spring NW,1 Bentonite Spring NW,1	NE 8 20S 44E Outcrop	Mill run - Channel 0-6 V Channel 6-10 V	6.60 120 6.92 80 6.22 60	40 13.54 - 300 >10.00 -	25.0 17.0 42.0 17.0 39.0 15.5	tr m	tr		tr	12.80 3.10 0.93 0.40 <0.01 17.24 32.90 8.20 3.30 0.70 0.09 45.19 31.90 22.90 7.38 0.49 0.08 62.75	6.54 15.60 6.92 0.23 29.29	
92 Mali 93 Mali 94 Mali	heur Double Mtn. 7.5 heur Grassy Mtn. 7.5 heur Grassy Mtn. 7.5	Bentonite Spring NE,1 Lowe Springs NE,1		Shallow pit - Channel 0-6 V Channel 0-10 V	7.43 150 6.68 120 7.56 70	420 >10.00 4.09 40 9.27 - 750 5.99 4.46	22.5 12.0 33.0 12.5	m m		tr m		55.70 11.30 1.87 1.21 0.04 70.12 18.60 7.40 2.58 0.42 <0.01 29.01 24.30 2.67 1.29 0.35 <0.01 28.62	4.65 21.90 10.60 0.17 37.32	26.41 24.90 7.70 0.68 59.69 93 28.95 24.57 11.89 0.52 65.93 94
95 Mali	heur Adrian 7.5	Teague's mill NE,S	SE 33 21S 44E Outcrop SW 27 21S 46E Bentonite mill	Grab 0-3 V Mill run(SG-40) -		640 3.58 0.82	28.0 16.0 24.0 7.0	m	tr			16.20 2.59 0.41 0.36 <0.01 19.57		38.80 41.49 6.09 0.99 87.37 96
97 Mall 98 Harr 99 Harr 100 Mall	ney Upton Mtn. 7.5 ney Upton Mtn. 7.5	Teague's mill NE, S Wm. Sprgs. Reservoir NE, S Wm. Sprgs. Reservoir NE, I Grassy Mtn. SW, I	NE 8 22S 36E Arroyo cut	Mill run(CS-90) - Channel 0-4 V Channel 0-4 V Grab -	10.84 80	>840 0.96 - 160 6.30 - 180 >10.00 - - 2.72	9.5 6.5 24.0 9.5 33.5 9.0 TE 59.0	m M m			tr	8.80 1.65 0.38 0.70 0.01 11.54 3.51 0.91 0.48 0.49 0.01 5.40	2.94 35.50 5.35 0.95 44.74	11.74 37.15 5.73 1.65 56.27 98 4.84 32.81 14.68 1.28 53.61 99
101 Mall 102 Harr	heur Grassy Mtn. 7.5	Oxbow Basin SE,	SW 28 22S 44E Outcrop	Channel 0-5 V Shallow pit -	4.33 40 9.61 140	80 7.25 - 540 0.51 -	34.5 15.0 41.0 13.0	m m	tr - tr	tr -	m - tr		0.23 38.00 8.80 0.38 47.41	5.29 53.80 12.69 1.27 73.05 102
103 Harr 104 Mall 105 Mall	heur Winnemucca Creek 7.5	Wm. Sprgs. Reservoir NE, Sw., I Wm. Sprgs. Reservoir SW, I Dry Arm NW, I	NE 22 23S 37E Road cut	Shallow pit - Channel 0-3 V Shallow pit -	11.52 170	720 >10.00 - 510 3.38 - 240 >10.00 -	24.5 12.0 30.0 10.0 77.0 36.0	m m tr		tr -	- tr - tr - m -	4.34 1.51 0.59 0.96 0.01 7.41	0.53 40.70 11.90 0.82 53.95	
107 Mall	heur Twin Springs 7.5 heur Twin Springs 7.5 heur Twin Springs 7.5	Dry Arm NE,1 Twin Springs SW,3 Dry Arm SW,1	SW 1 23S 43E Outcrop	Shallow pit - Shallow pit - Channel 0-8 V	1.87 0 9.38 230 1.98 0	40 >10.00 - 840 4.27 3.73 100 3.33 -	141.0 73.0 14.0 9.5 75.0 46.0	tr m tr	M m - m M	- tr	tr	8.90 11.30 5.44 0.31 0.05 26.00 3.66 10.20 4.27 0.21 <0.01 18.35	3.51 14.90 4.51 0.15 23.07 0.15 5.06 1.98 0.26 7.45	
109 Mali 110 Mali	heur Twin Springs 7.5 heur Twin Springs 7.5	Dry Arm SW,1 Dry Arm SW,1	•	Channel 16-24 V Channel 0-6 V	1.74 0 1.57 0	160 >10.00 - 60 >10.00 -	79.0 46.0 96.0 60.0	tr tr	M	-	M - tr -	3.79 9.20 7.85 0.14 <0.01 20.99	0.05 3.94 2.73 0.17 6.89	3.37 40.66 7.36 0.40 51.79 109 3.84 13.14 10.58 0.31 27.87 110
	-			Shallow pit -	12.10 420 9.47 160	>840	8.5 7.5 7.0 7.0 35.0 14.5 52.0 18.5	m M m M		 m -		11.70 9.80 1.63 0.33 0.01 23.47 38.90 39.20 8.23 1.74 0.04 88.11 37.50 77.90 2.48 1.44 0.02 119.34 23.20 9.70 2.95 2.20 0.01 38.06	2.97 3.61 0.59 0.36 7.53 1.74 34.00 0.98 0.18 36.90	39.24 111.90 3.46 1.62 156.22 113
115 Harr	ney Crane 15	Wrights Point SW,1	NW 33 24S 31E Road cut SW 20 24S 43E Outcrop	Grab - Channel 0-3 V			TE TE	 - m	tr	tr -	n	1.83 0.16 0.28 0.14 <0.01 2.42	5.16 15.40 8.13 1.50 30.19	6.99 15.56 8.41 1.64 32.60 115 37.50 18.40 9.50 1.27 66.67 116
117 Mali 118 Mali 119 Mali	heur Diamond Butte 7.5 heur Quartz Mt. Basin 7.5	Red Butte NE,	SW 33 25S 43E Outcrop SW 22 25S 43E Outcrop	Shallow pit - Channel 0-4 V Channel 0-4 V	5.82 180 3.01 20	100 4.51 -	11.0 9.0 66.5 44.0	M m tr		: :		26.40 6.80 9.26 0.35 0.02 42.83 45.90 9.00 4.54 0.63 0.04 60.11 16.70 17.50 25.60 0.55 0.01 60.36	6.47 10.90 4.58 0.29 22.24 0.49 4.49 6.01 0.31 11.30	52.37 19.90 9.12 0.92 82.31 118 17.19 21.99 31.61 0.86 71.65 119
120 Mali	heur Diamond Butte 7.5		NE 16 26S 43E Outcrop	Grab - Channel 0-10 V	7.62 200	>840 1.18 0.61		tr m				51.10 8.90 1.73 1.43 0.01 63.17	6.12 27.60 3.49 0.57 37.78	
122 Mall 123 Mall 124 Mall 125 Mall	heur Diamond Butte 7.5	Red Butte NW,: Diamond Butte NW,	SW 15 26S 43E Outcrop SW 3 26S 43E Outcrop NW 23 26S 43E Outcrop NW 23 26S 43E Outcrop	Channel 0-5 V Channel 0-15 V Shalow pit - Channel 0-6 V	6.22 220	180 11.04 8.03 680 0.17 0.15 180 2.38 2.07 740 2.74 1.49	12.5 10.0	m M M	m	m -		17.20 11.30 1.89 0.72 0.05 31.16	17.90 12.10 6.76 0.63 37.39 10.90 12.80 1.72 0.48 25.90	89.90 18.20 10.89 1.47 120.46 123
126 Mali 127 Mali	heur Diamond Butte 7.5	Diamond Butte SE,, Red Butte NW,	SE 35 26S 43E Outcrop NW 13 26S 43E Outcrop	Channel 0-5 V Shallow pit -		840 0.04 <0.01		m M	- tr m	m -	tr - n		9.12 15.00 2.70 1.45 28.27	24.82 22.80 4.33 2.35 54.30 127
128 Mali 129 Mali 130 Harr	heur Rockville 7.5	Rockville School SE,; Rockville School SE,; Harney Lake SE,;	•	Grab - Shallow pit - Shallow pit -	9.42 220 9.56 260 5.91 500	>840 1.09 1.30 240 2.10 1.25 740 22.02 14.13	9.0 8.0	m M tr	tr tr - tr	tr - m tr 	- tr - tr celestite - M	13.30 16.90 2.79 1.04 0.02 34.05 12.40 20.30 3.12 1.77 0.03 37.62 13.30 16.40 120.00 0.14 1.28 151.12	5.29 22.00 1.82 0.96 30.07 7.18 15.30 1.53 1.09 25.10 1.07 9.84 10.20 0.15 21.26	19.58 35.60 4.65 2.86 62.69 129
131 Harr 132 Harr 133 Harr	ney SE Harney Lake 7.5	Harney Lake C Harney Lake C S. Fork Reservoir SE,	13 27S 31E Road cut 24 27S 31E Road cut NW 10 28S 36E Outcrop	Grab - Shallow pit - Shallow pit -	3.53 0 7.18 130 7.42 0	0 >10.00 - 430 >10.00 - 40 >10.00 -	75.0 93.0 49.0 15.5 113.0 40.0	- n	 	- M tr M 		10.00 0.53 4.05 0.60 0.07 15.25 27.20 7.20 10.00 0.42 0.09 44.91 1.42 0.82 0.40 0.35 <0.01 3.00	42.60 2.49 0.89 2.48 48.46 10.20 24.80 11.20 0.43 46.63 0.24 16.30 5.06 0.81 22.41	37.40 32.00 21.20 0.85 91.45 132 1.66 17.12 5.46 1.16 25.40 133
134 Harr 135 Harr	ney S. Fork Reservoir 7.5	S. Fork Reservoir NW, S. Fork Reservoir SE,	NW 10 28S 36E Outcrop NW 10 28S 36E Outcrop	Grab - Drill cuttings 0-2 H	4.81 0 6.93 0	40 >10.00 - 0 15.88 -	66.0 25.0 82.0 60.0	n n	tr	: :	tr tr	1.46 0.43 0.28 0.11 0.01 2.29 1.03 0.49 0.20 0.14 <0.01 1.87	0.61 16.60 7.38 0.57 25.16 0.45 9.62 3.27 0.59 13.93	2.07 17.03 7.66 0.68 27.44 134 1.48 10.11 3.47 0.73 15.79 135
136 Harr 137 Harr 138 Harr	ney S. Fork Reservoir 7.5 ney S. Fork Reservoir 7.5	S. Fork Reservoir SE, S. Fork Reservoir SE, S. Fork Reservoir SE,	NW 10 28S 36E Outcrop NW 10 28S 36E Outcrop	Drill cuttings 2-4 H Drill cuttings 4-6 H Drill cuttings 6-8 H	6.78 0 6.77 0 6.73 0	0 15.00 - 20 19.17 - 0 >10.00 -	60.0 44.0 54.0 44.0 49.0 40.0	m m			tr	1.00 0.48 0.20 0.12 <0.01 1.81 0.95 0.56 0.22 0.15 <0.01 1.89 1.03 0.58 0.23 0.18 <0.01 2.03	0.52 9.81 3.52 0.81 14.66 0.50 9.07 3.20 0.82 13.59 0.46 8.94 3.12 0.75 13.27	1.45 9.63 3.42 0.97 15.47 137 1.49 9.52 3.35 0.93 15.29 138
139 Harr 140 Harr	ney S. Fork Reservoir 7.5	S. Fork Reservoir SE, S. Fork Reservoir SE, Rome SE,	NW 10 28S 36E Outcrop	Drill cuttings 8-8.5 H Drill cuttings 8.5-9 H	6.49 0 5.02 0 6.68 40	0 9.49 - 0 9.70 -	52.0 43.5 74.0 -	M M	: : :		tr	1.07 0.51 0.21 0.17 <0.01 1.97 1.14 0.41 0.17 0.18 <0.01 1.91 24.40 3.04 9.64 2.15 0.07 39.30	0.31 8.55 3.15 0.72 12.73	1.45 8.96 3.32 0.90 14.63 140
141 Mali 142 Mali 143 Mali 144 Lake	heur Burns Junctions 7.5 heur Burns Junctions 7.5	Rome SE; Crooked Creek SW Crooked Creek SW 5.5 Gold Cr./Lee Thomas Crossing SE;	12 32S 40E Road cut 12 32S 40E Road cut	Mine dump - Channel 0-6 V Channel 6-10 V Shallow pit -	6.68 40 6.77 40 6.70 20 7.90 40	120 0.22 - 120 >10.00 - 160 0.56 - 120 24.69 -	82.5 31.0 63.0 24.0 120.0 35.0	m tr M	m tr - tr m 	tr - tr -	tr	9.50 2.25 0.89 0.41 0.02 13.07 5.86 1.24 0.57 0.27 0.01 7.95 0.11 0.11 0.04 0.35 <0.01 0.62	4.88 25.40 7.09 1.34 38.71 5.57 13.50 5.29 0.98 25.34 0.07 18.40 6.52 0.82 25.81	14.38 27.65 7.98 1.75 51.76 142 11.43 14.74 5.86 1.25 33.28 143 0.18 18.51 6.56 1.17 26.42 144
145 Klar	math Altamount 7.5 ney Tumtum Lake 7.5	Klamath Falls SW Pueblo Mts. NE,	26 38S 8E Road cut NE 20 39S 35E Outcrop	Shallow pit - Shallow pit -	7.78 60 7.06 0	180 >10.00 - 20 50.70 10.59	TE 240.0 TE 90.0	 n	tr	 tr -	n	0.87 0.10 0.06 0.06 <0.01 1.10 3.54 0.50 0.41 0.41 0.03 4.89	0.49 10.60 10.90 0.35 22.34 3.69 25.60 7.13 1.43 37.85	1.36 10.70 10.96 0.41 23.43 145 7.23 26.10 7.54 1.84 42.71 146
147 Harr 148 Lake 149 Lake 150 Lake	e Strawberry Butte 15 e Drews Reservoir 7.5	Pueblo Mts. SW,: Dry Valley N,SI Drews Reservoir SW,: Drews Reservoir SW.:	5W 1 40S 16E Stream cut .SW 1 40S 17E Road cut	Channel 0-4 V Grab - Channel 0-3 V Channel 0-4 V	8.44 260 6.56 0 12.13 30 12.43 80	220 >10.00 - 80 10.20 - 110 15.11 - 120 17.89 -	10.0 10.5 TE 84.0 53.0 12.0 62.0 10.5	ш ш М М		tr - tr - - m - m	n	27.40 10.50 1.96 4.20 0.13 44.19 0.77 0.15 0.10 0.31 <0.01 1.34 0.93 0.35 0.12 0.17 <0.01 1.58 1.70 1.62 0.44 0.91 <0.01 4.68	14.30 13.20 0.81 3.92 32.23 0.36 18.20 9.26 0.74 28.56 3.36 33.70 7.85 0.70 45.61 0.57 32.60 8.42 0.27 41.86	1.13 18.35 9.36 1.05 29.89 148 4.29 34.05 7.97 0.87 47.18 149
150 Lake	heur Payne Creek 7.5	Opalite mine SW,: Hawsy Walksy NW,:	SE 29 40S 40E Outcrop	Shallow pit - Channel 0-20 H	9.55 140 6.63 0	820 15.03 - 20 >10.00 -	9.5 6.0 130.0 84.0	 m	 - tr	- tr	- tr	4.77 9.90 89.20 1.40 3.52 108.79 5.18 10.40 2.97 0.56 <0.01 19.12	1.81 29.90 14.30 0.71 46.72 0.72 13.60 3.44 0.88 18.64	6.58 39.80 103.50 2.11 151.99 151 5.90 24.00 6.41 1.44 37.75 152
153 Amer	rican Colloid Company's "Wyomin	g" type bentonite, "WDGII crude" bentonite, "standard base clay"				>840 - 3.20		M M	tr tr	 tr -	tr - tr - tr - tr -	8.50 1.62 0.93 0.17 0.01 11.23 13.9 3.00 1.94 0.20 0.01 19.05	46.10 14.20 7.20 1.42 68.92 36.60 14.40 7.05 0.90 58.95	

^{*} Because of technical considerations, the percentage of expansion was determined by measuring the change in volume (total volume less 8 ml) divided by 5 grams times 100. The 5 grams was assumed to have a volume of 8 ml.

TE = Total expelled: >350 ml M = Major portion of sample m = minor portion of sample tr = trace